



US009167704B2

(12) **United States Patent**
Hrametz et al.

(10) **Patent No.:** **US 9,167,704 B2**
(45) **Date of Patent:** **Oct. 20, 2015**

(54) **LEAD-FREE SOLDER ALLOY FOR PRINTED
CIRCUIT BOARD ASSEMBLIES FOR
HIGH-TEMPERATURE ENVIRONMENTS**

USPC 420/560; 29/840
IPC B23K 35/262; C22C 13/00
See application file for complete search history.

(75) Inventors: **Andy A. Hrametz**, Houston, TX (US);
Alex T. Duncan, Houston, TX (US)

(56) **References Cited**

(73) Assignee: **Halliburton Energy Services, Inc.**,
Houston, TX (US)

U.S. PATENT DOCUMENTS

(*) Notice: Subject to any disclaimer, the term of this
patent is extended or adjusted under 35
U.S.C. 154(b) by 262 days.

5,346,775 A * 9/1994 Jin et al. 428/614
2005/0100474 A1* 5/2005 Huang et al. 420/560
2005/0151233 A1 7/2005 Deepak et al.
2011/0052444 A1* 3/2011 Hrametz et al. 420/504

FOREIGN PATENT DOCUMENTS

(21) Appl. No.: **12/517,652**

CA 2641812 C 6/2008
WO WO-2005099961 A1 10/2005
WO WO 2005099961 A1 * 10/2005
WO 2008073090 A1 6/2008
WO WO-2008073090 A1 6/2008

(22) PCT Filed: **Dec. 13, 2006**

(86) PCT No.: **PCT/US2006/047586**

§ 371 (c)(1),
(2), (4) Date: **Jun. 4, 2009**

OTHER PUBLICATIONS

(87) PCT Pub. No.: **WO2008/073090**

“European Application Serial No. 06849954.0, Extended European
Search Report mailed Nov. 24, 2010”, 6 pgs.

PCT Pub. Date: **Jun. 19, 2008**

(Continued)

(65) **Prior Publication Data**

US 2011/0052444 A1 Mar. 3, 2011

Primary Examiner — Weiping Zhu

(74) *Attorney, Agent, or Firm* — Schwegman Lundberg &
Woessner, P.A.; Benjamin Fite

(51) **Int. Cl.**

H05K 3/34 (2006.01)
B23K 35/26 (2006.01)
C22C 13/00 (2006.01)

(57) **ABSTRACT**

(52) **U.S. Cl.**


CPC **H05K 3/3463** (2013.01); **B23K 35/262**
(2013.01); **C22C 13/00** (2013.01); **H01L**
2924/0002 (2013.01)

A solder alloy suitable for high temperature environments,
such as for example electronic systems used in an oil or gas
well where the temperature may be in the region of 175° C.,
the solder alloy having a Silver weight % in the range of 3.5
to 7.0, a Copper weight % in the range of 1.0 to 4.0, and an
Antimony weight % in the range of 1.0 to 3.0. Other embodi-
ments are described and claimed.

(58) **Field of Classification Search**

CPC H05K 3/3463; B23K 35/262

5 Claims, 2 Drawing Sheets



(56)

References Cited

OTHER PUBLICATIONS

"Canadian Application Serial No. 2,641,812, Response filed Dec. 10, 2013 to Office Action mailed Jun. 12, 2013", 10 pgs.

"Canadian Application Serial No. 2,641,812, Office Action mailed Jun. 12, 2013", 2 pgs.

"European Application Serial No. 06849954.0, Office Action mailed Dec. 13, 2010", 1 pg.


"European Application Serial No. 06849954.0, Response filed Jun. 13, 2011 to Office Action mailed Dec. 13, 2010", 14 pgs.

"International Application Serial No. PCT/US2006/047586, International Preliminary Report on Patentability dated Jun. 16, 2009", 4 pgs.

"International Application Serial No. PCT/US2006/047586, International Search Report mailed Nov. 16, 2007", 1 pg.

"International Application Serial No. PCT/US2006/047586, Written Opinion mailed Nov. 16, 2007", 3 pgs.

* cited by examiner



(PRIOR ART)

FIG. 1




FIG. 2




FIG. 3




FIG. 4

1

LEAD-FREE SOLDER ALLOY FOR PRINTED CIRCUIT BOARD ASSEMBLIES FOR HIGH-TEMPERATURE ENVIRONMENTS

FIELD

Embodiments of the present invention relate to solder alloys.

BACKGROUND

Solder is a ubiquitous product used in the electronic industry to attach electronic components, such as integrated circuit packages and passive components, to circuit boards, to electrically connect such electronic components to traces on a circuit board in order to realize electronic systems, and to help dissipate heat.

In some applications, electronic systems are expected to survive harsh conditions. For example, in the oil well logging industry, various tools are employed to investigate formation conditions, and such tools often employ sophisticated electronic systems. Wireline logging tools, logging-while-drilling tools, and other types of downhole tools often operate at temperatures from 150° C. to 175° C.

Lead (Pb) has long been a component of solder used in the electronic industry. Some governing bodies, such as the European Union, have banned solder in which lead is a component because of the concern that the lead may pose an environmental and health hazard. It is expected that other governing bodies, or governments, may place taxes, restrictions, or bans on solder with lead. Because of this, there has been much research in developing lead-free solder for the electronics industry.

Accordingly, it is useful to provide a lead-free solder alloy suitable for high-temperature environments.

BRIEF DESCRIPTION OF THE DRAWINGS

FIG. 1 illustrates a prior art normal solder joint.

FIG. 2 illustrates a prior art solder joint with damage due to high temperature.

FIG. 3 illustrates a well logging tool employing an embodiment of the present invention.

FIG. 4 illustrates a thermal analysis curve for an embodiment using differential scanning calorimetry.

DESCRIPTION OF EMBODIMENTS

In the descriptions that follow, the scope of the term “some embodiments” is not to be so limited as to mean more than one embodiment, but rather, the scope may include one embodiment, more than one embodiment, or perhaps all embodiments.

High temperature thermal cycling and heat exposure commonly cause damage to a solder joint, generally resulting in changes to the solder microstructure over time, even though its appearance may seem the same. Changes to the solder microstructure usually affect the properties of the solder and the solder joint itself. Some known lead-free solders containing very large percentages of Tin (Sn) exhibit strong IMC (intermetallic compound) bonding and good IMC development, but it has been found that for some of these known solder alloys, exposure to temperatures in the region of 175° may accelerate rapid growth of and changes in the microstructure interfaces and in the IMC layers. The rapid intermetallic growth between interfacial layers creates diffusion

2

voiding adjacent to the component leads and solder pads, which reduces the solder joint strength in these areas.

FIGS. 1 and 2 are simplified illustrations of typical photomicrographs of a solder joint. FIG. 1 illustrates a solder joint without damage. In FIG. 1, an integrated circuit (IC) package with a copper lead frame is soldered to a copper land solder pad. The copper land solder pad is formed on an epoxy circuit board. FIG. 1 also illustrates an IMC layer. FIG. 2 illustrates typical damage that may occur to a solder joint at high temperature, such as for example 185° C. In FIG. 2, copper depletion is indicated, as well as extreme IMC growth. Furthermore, Kirkendall voids are indicated in FIG. 2.

It has been found that solder alloy having a range of 3.5 to 7.0 weight % Silver (Ag), a range of 1.0 to 4.0 weight % Copper (Cu), a range of 1.0 to 3.0 weight % Antimony (Sb), and where the remainder is Sn, has desirable properties in a high temperature environment, such as the environment experienced by a well logging tool. It is found that such solder alloys have a melting temperature above 175° C., and for some embodiments, the melting temperature is around 220° C. Such solder alloys have a relatively wide plastic range, i.e., the difference in liquidus and solidus temperatures may be relatively large for such solder alloys. However, this is not a problem in the high temperature environment of an oil or gas well.

As an example of a particular embodiment, a solder alloy may consist of 4.7 weight % Ag, 1.7 weight % Cu, 1.5 weight % Sb, and 92.1 weight % Sn. An example of a thermal analysis curve for such an embodiment is illustrated in FIG. 4, where the sample mass is 7.9 mg. The thermal analysis curve in FIG. 4 was obtained by differential scanning calorimetry. Line 402 may serve as a reference, indicating the heat flow when the sample is not experiencing a change in state. The sample is heated up in an adiabatic chamber with a reference sample that does not change state over the temperature measurement range. The x-axis is the temperature of the reference sample in units of Celsius, and the y-axis measures heat flow in or out of the sample in units of watts/gram. Solidus is at around 219.5° C., where the sample begins to melt. Because in general heat capacity increases at a phase transition, above the solidus, it is seen that the heat flow into the sample increases rapidly. The heat flow is negative, indicating that heat is flowing into the sample (endothermic). Line 404 is a tangent to curve 406, and the intersection of line 404 with reference line 402 may be taken as the melting point, which is about 220.32° C. As the sample is heated, it eventually turns into a liquid, where the liquidus is seen to be at around 232° C.

It is found that the addition of Sb slightly increases the solidus temperature. It is found that having more Cu may slow down IMC layer formation. The inclusion of Sb is found to make the solder stronger. That is, there is greater ductile strength and better resistance to degradation so that changes in the solder properties due to time and temperature are mitigated. In addition to the above-cited elements, some embodiment solder alloys may have a trace amount of Zinc (Zn) in the range of 0.1 to 1.0 weight %. It has been found that Zn may slow down the formation of Kirkendall voids.

Standard techniques may be employed to manufacture the above-described embodiments into a solder paste. It is expected that the above-described embodiments may be used for solder in surface mount technology (SMT), or through-hole technology, and for various IC packages, such as ball grid array (BGA) packages, framelead and leadless frame packages, dual in-line packages (DIPs), small outline integrated circuits (SOICs), quad flat packages (QFPs), and chip scale packages (CSPs), to name a few. The above-described

embodiments may also be used for passive and active components. Standard techniques may also be employed to manufacture wire-form solder having the disclosed compositions.

Before components are soldered to a board, the leads are often coated with a protective finish. The protective finish may need to be removed before soldering with an embodiment solder if there are elements in the protective finish that are not compatible with the embodiment solder. That is, the presence of some elements in the protective finish may degrade the resulting solder joint. For example, it is found that Indium, Lead, or Gold in a protective finish is not compatible. If the protective finish is not compatible, then it should be stripped off of the leads. Some protective finishes need not be removed, however. For example, a protective finish consisting of only Sn need not be removed.

It is expected that embodiments of the present invention may find application to various electronic systems used in relatively high temperature environments. As a particular example, it is expected that embodiments of the present invention may find application in electronic systems used in a well logging tool. Such an example application is illustrated in simple fashion in FIG. 3, where logging tool **302** in well hole **304** measures various physical properties of formation **306**. Well logging tool **302** may be a wireline tool, where wire **308** provides various signal information to instruments on the surface (not shown).

Various modifications may be made to the disclosed embodiments without departing from the scope of the invention as claimed below.

What is claimed is:

1. A premelted solid lead-free wire-form solder for use in forming solder joints in an electronic system of a well logging tool, the lead-free wire-form solder having a preliminary solid alloy composition comprising:

Silver;
Copper;
Antimony; and
Tin;

wherein the solder alloy composition has a weight % of the Silver in a range of 3.5 to 7.0, a weight % of the Copper in a range of 1.0 to 4.0, and a weight % of the Antimony in a range of 1.0 to 3.0, and the remainder Tin.

2. The premelted solid lead-free wire-form solder as set forth in claim **1**, wherein the preliminary solid solder alloy composition comprises about 4.7 weight % Silver, about 1.7 weight % Copper, and about 1.5 weight % Antimony, and the remainder Tin.

3. The premelted solid lead-free wire-form solder as set forth in claim **1**, wherein the preliminary solid solder alloy composition has a weight % of the Tin in a range of 86.0 to 94.5.

4. The premelted solid lead-free wire-form solder of claim **1**, wherein the preliminary solder alloy composition further comprises at least 0.1 weight % Zinc.

5. The premelted solid lead-free wire-form solder as set forth in claim **4**, wherein the preliminary solder alloy composition comprises a weight % of the Zinc in a range of 0.1 to 1.0.

* * * * *