



US009180727B2

(12) **United States Patent**
Park et al.

(10) **Patent No.:** **US 9,180,727 B2**
(45) **Date of Patent:** **Nov. 10, 2015**

(54) **DECORATION SHEET WITH HIGH WEATHER RESISTANCE AND HAIR LINE**

B29C 45/14; B29C 2791/00; B29C 2791/001;
B29C 2745/14811; B44C 1/005; B44C 3/085;
B44C 5/04; B29L 2009/00; B29L 2009/003;
B29L 2031/722; B29K 2705/00; G03H
2001/0284

(75) Inventors: **Jiyong Park**, Ulsan (KR); **Donggon Kim**, Ulsan (KR); **Jungeun Ha**, Gyeongsangnam (KR)

USPC 156/230, 247; 428/195.1, 201, 327, 354
See application file for complete search history.

(73) Assignee: **LG Hausys, Ltd.**, Seoul (KR)

(*) Notice: Subject to any disclaimer, the term of this patent is extended or adjusted under 35 U.S.C. 154(b) by 0 days.

(56) **References Cited**

U.S. PATENT DOCUMENTS

4,133,913 A * 1/1979 Moore 427/140
6,544,369 B1 * 4/2003 Kitamura et al. 156/230

(21) Appl. No.: **13/503,820**

(22) PCT Filed: **Dec. 7, 2010**

FOREIGN PATENT DOCUMENTS

(86) PCT No.: **PCT/KR2010/008707**

JP 1988-037953 2/1988
JP 1998-071677 3/1998

§ 371 (c)(1),
(2), (4) Date: **Apr. 24, 2012**

(Continued)

(87) PCT Pub. No.: **WO2011/074820**

OTHER PUBLICATIONS
JP 2005-246891 Machine Translation via AIPN Website translation tool.*

PCT Pub. Date: **Jun. 23, 2011**

(Continued)

(65) **Prior Publication Data**

US 2012/0213981 A1 Aug. 23, 2012

Primary Examiner — Mark Ruthkosky

Assistant Examiner — Laura C Powers

(30) **Foreign Application Priority Data**

Dec. 17, 2009 (KR) 10-2009-0125953

(74) *Attorney, Agent, or Firm* — Dentons US LLP

(51) **Int. Cl.**

B44C 1/10 (2006.01)

B44C 5/00 (2006.01)

(Continued)

(57) **ABSTRACT**

Provided is a decoration sheet with high weather resistance and hair line, and a manufacturing method thereof. The decoration sheet with weather resistance and hair line, which is attached to a surface of an object so as to protect the object from external environment, includes a PVC layer of which a lower surface is attached to the object; a hair line printing layer formed with a lower surface contacted with an upper surface of the PVC and an upper surface on which the hair line is formed, and formed of a mixture of aluminum and acrylic; and an acrylic layer formed with a lower surface contacted with an upper surface of the hair line printing layer and an upper surface exposed to the external environment.

(52) **U.S. Cl.**


CPC **B44C 1/105** (2013.01); **B29L 2009/003** (2013.01); **B32B 15/08** (2013.01);

(Continued)

3 Claims, 1 Drawing Sheet

(58) **Field of Classification Search**

CPC **B32B 15/08**; **B32B 27/08**; **B32B 27/30**; **B32B 15/20**; **B32B 2311/00**; **B32B 2451/00**;



(51)	Int. Cl.		JP	2000-211070	A	8/2000
	<i>B32B 15/08</i>	(2006.01)	JP	2002-210877	A	7/2002
	<i>B32B 15/20</i>	(2006.01)	JP	2004-142439		5/2004
	<i>B32B 27/08</i>	(2006.01)	JP	2005-096266		4/2005
	<i>B32B 27/30</i>	(2006.01)	JP	2005-246891		9/2005
	<i>B32B 38/06</i>	(2006.01)	KR	10-2006-0012072	A	2/2006
	<i>B29L 9/00</i>	(2006.01)	KR	10-0816300	B1	3/2008
			KR	10-2008-0066272	A	7/2008
(52)	U.S. Cl.		KR	10-2009-0030932	A	3/2009
	CPC	<i>B32B 15/20</i> (2013.01); <i>B32B 27/08</i>	KR	1020100047382	A	5/2010
		(2013.01); <i>B32B 27/30</i> (2013.01); <i>B32B 38/06</i>	WO	2010/008225	A2	1/2010
		(2013.01); <i>B44C 5/00</i> (2013.01); <i>Y10T</i>				
		<i>428/24851</i> (2015.01)				

OTHER PUBLICATIONS

(56)	References Cited		JP 10-071677	Machine Translation via AIPN Website translation tool.*	
		FOREIGN PATENT DOCUMENTS	JP 2004-142439	Machine Translation via AIPN Website translation tool.*	
		JP	11-020078	A	1/1999
		JP	11-105206	A	4/1999

* cited by examiner

Fig. 1

100





Fig. 2



1

DECORATION SHEET WITH HIGH WEATHER RESISTANCE AND HAIR LINE

This application is a National Stage Entry of International Application No. PCT/KR2010/008707, filed Dec. 7, 2010, and claims the benefit of Korean Application No. 10-2009-0125953, filed on Dec. 17, 2009, which is hereby incorporated by reference for all purposes as if fully set forth herein.

TECHNICAL FIELD

The present invention relates to a decoration sheet attached to an object, and particularly to a decoration sheet with high weather resistance and hair line, which has the weather resistance protecting the object from the external environment such as ultraviolet ray and moisture, and the hair line providing an effect of metallic feeling. Further, the present invention relates to a manufacturing method thereof.

BACKGROUND ART

Generally, a building has a window system for both lighting and ventilating purposes. The window system includes a window sash which is directly installed at the building, and a window which is coupled to the window sash in a hinged or sliding manner. The window includes a frame which is coupled to the window sash, and a glass plate which is fixed to the frame.

Typically, a decoration sheet with high weather resistance is attached to outer surfaces of the window sash and frame which are exposed outside the building. Because the decoration sheet functions to protect the window sash and frame from the external environment such as ultraviolet ray and moisture, it has high weather resistance against the ultraviolet ray, moisture and the like.

Meanwhile, in order to provide an esthetic appearance of the window sash and frame, the decoration sheet having an effect of metallic feeling is recently required by the market. For this end, there have been provided a decoration sheet in which hair line is formed on a PVC sheet and a decoration sheet in which hair line is formed on a PET sheet. In case of the former, there are limitations in providing the effect of metallic feeling, and in case of latter, the weather resistance of PET is too low, and thus it is improper as the decoration sheet with the weather resistance.

In Japanese Patent Laid-Open No. 2004-142439, there is disclosed a metallic luster sheet having metallic feeling as well as weather resistance. The metallic luster sheet includes a base sheet which is contacted with an object, a fine unevenness layer stacked on an upper surface of the base sheet, and a protecting sheet stacked on an upper surface of the fine unevenness layer. The base sheet is formed of acryl, PVC, PET and so on, the metallic luster sheet is formed of aluminum, nickel, chrome and the like, the fine unevenness layer is formed of acryl, PVC and the like, and the protecting sheet is formed of acryl and the like.

The metallic luster sheet includes a metallic luster layer formed of a metallic material, and the hair line is formed at the metallic luster layer so as to provide the effect of metallic feeling. Further, the base sheet and the protecting sheet are provided on both upper and lower surfaces of the metallic luster layer so as to provide the high weather resistance.

However, in the metallic luster sheet as described above, the hair line is formed on the metallic luster layer formed of aluminum, nickel, chrome and the like through the fine unevenness layer. Therefore, in the metallic luster sheet, there

2

is a problem in that the fine unevenness layer has to be necessarily provided between the metallic luster layer and the protecting layer.

Furthermore, in the metallic luster sheet as described above, since the metallic luster layer formed of the metallic material is contacted with the fine unevenness layer and base sheet which are formed of a polymer resin, there is another problem in that adhesive strength between the metallic luster layer and the fine unevenness layer and between the metallic luster layer and the base sheet is not ensured sufficiently.

DISCLOSURE OF INVENTION

Technical Problem

An embodiment of the present invention is directed to providing a decoration sheet with high weather resistance and hair line, which can be manufactured to have a simple structure and also can enhance the adhesive strength between a metallic sheet and a non-metallic sheet adjacent to the metallic sheet.

Another embodiment of the present invention is directed to providing a manufacturing method of the decoration sheet with high weather resistance and hair line.

Solution to Problem

To achieve the object of the present invention, the present invention provides a decoration sheet with weather resistance and hair line, which is attached to a surface of an object so as to protect the object from external environment, including a PVC layer of which a lower surface is attached to the object; a hair line printing layer formed with a lower surface contacted with an upper surface of the PVC and an upper surface on which the hair line is formed, and formed of a mixture of aluminum and acryl; and an acrylic layer formed with a lower surface contacted with an upper surface of the hair line printing layer and an upper surface exposed to the external environment.

Preferably, the hair line printing layer has a thickness of 3~10 μ .

Further, the present invention provides a manufacturing method of a decoration sheet with weather resistance and hair line, which is attached to a surface of an object so as to protect the object from external environment, including forming the hair line at a surface of a transfer film; coating a coating liquid, in which liquid aluminum and acrylic medium are mixed, on the surface of the transfer film on which the hair line is formed, and then hardening the coating liquid; thermally transferring the transfer film onto a PVC sheet so as to contact the hardened coating liquid and the PVC sheet, and then removing the transfer film; and stacking an acrylic film on a surface of the hardened coating liquid.

Preferably, in the coating of the coating liquid on the surface of the transfer film, the coating liquid has a thickness of 3~10 μ .

Preferably, in the thermally transferring of the transfer film onto a PVC sheet, the transfer film is thermally transferred onto the PVC sheet at a temperature of 110~170° C.

Preferably, a content of the acrylic medium is within an extent of 75~98% based on the whole weight.

BRIEF DESCRIPTION OF DRAWINGS

FIG. 1 is a cross-sectional view of a decoration sheet with high weather resistance and hair line according to the present invention.

FIG. 2 is a schematic view showing a manufacturing process of the decoration sheet of FIG. 1.

DETAILED DESCRIPTION OF MAIN ELEMENTS

100: decoration sheet **110:** PVC layer
130: hair line printing layer **150:** acrylic layer
210: transfer film **220:** coating liquid
230: PVC sheet **240:** acrylic film

MODE FOR THE INVENTION

The advantages, features and aspects of the invention will become apparent from the following description of the embodiments with reference to the accompanying drawings, which is set forth hereinafter. The terms and words used in the description as described below are not limited to the typical or dictionary definition, and they can be interpreted as proper meanings and definitions consistent with the technical ideas.

FIG. 1 is a cross-sectional view of a decoration sheet with high weather resistance and hair line according to the present invention, and FIG. 2 is a schematic view showing a manufacturing process of the decoration sheet of FIG. 1.

A decoration sheet **100** with high weather resistance and hair line according to the present invention is attached to a surface of an object such as a window sash and a frame of a window in order to protect the object from the external environment such as ultraviolet ray and moisture. As shown in FIG. 1, the decoration sheet **100** with high weather resistance and hair line includes a PVC layer **110**, a hair line printing layer **130** and an acrylic layer **150**.

The PVC layer **110** is the lowermost layer of the decoration sheet **100**, and a lower surface of the PVC layer **110** is attached to the object. Further, the PVC layer **110** is made of PVC in order to ensure the weather resistance.

The hair line printing layer **130** is stacked on the PVC layer **110**. A lower surface of the hair line printing layer **130** is contacted with an upper surface of the PVC layer **110**, and the hair line is formed at an upper surface of the hair line printing layer **130**. The hair line printing layer **130** is formed of a mixture of aluminum and acryl.

In case that the hair line printing layer **130** contains aluminum and the hair line is formed at the upper surface of the hair line printing layer **130**, the decoration sheet **100** may have an effect of metallic feeling. Further, since aluminum is cheaper than other metallic materials, the decoration sheet **100** may be manufactured at low cost, if the hair line printing layer **130** is formed of aluminum.

If the hair line printing layer **130** is formed of only aluminum, the weather resistance of the hair line printing layer **130** is deteriorated. And, the adhesive strength between the hair line printing layer **130** of the metallic material and the PVC layer **110** of the non-metallic material and between the hair line printing layer **130** of the metallic material and the acrylic layer **150** of the non-metallic material is also deteriorated. Therefore, the acryl is used together with the aluminum as the material forming the hair line printing layer **130**. Since the acryl has the high weather resistance, if acryl is contained in the material forming the hair line printing layer **130**, the hair line printing layer **130** can have the weather resistance as well as the effect of metallic feeling. Further, since the acryl is non-metallic material, if the acryl is contained in the material forming the hair line printing layer **130**, it is possible to ensure the adhesive strength between the hair line printing layer **130** and the PVC layer **110** and between the hair line printing layer **130** and the acrylic layer **150**.

Preferably, the hair line printing layer **130** has a thickness of 3-10 μm . If the thickness of hair line printing layer **130** is less than the minimum value, it is difficult to form the hair line printing layer **130**, and if the thickness thereof is larger than the maximum value, the material thereof is wasted.

The acrylic layer **150** is the uppermost layer of the decoration sheet **100**. A lower surface of the acrylic layer **150** is contacted with the upper surface of the hair line printing layer **130**, and an upper surface thereof is exposed to the external environment. Further, the acrylic layer **150** is formed of the acryl in order to ensure the weather resistance.

Hereinafter, a manufacturing method of the decoration sheet **100** will be described with reference to FIG. 2.

The manufacturing method of the decoration sheet **100** with high weather resistance and hair line includes first to fourth steps (S110 to S140).

In the first step S110, the hair line is formed on a surface of a transfer film **210**. The transfer film **210** is formed of a material, which can facily form the hair line, for example, PET (Polyethylene Terephthalate).

In the second step S120, coating liquid **220** in which liquid aluminum and acrylic medium are mixed is coated on the surface of the transfer film **210** on which the hair line is formed, and then the coating liquid **220** is hardened. The acrylic medium is a liquid material in which acryl and a solvent are mixed. The solvent is evaporated when the coating liquid **220** is hardened. Therefore, the hardened coating liquid **220** contains only the aluminum and acryl.

The acrylic medium ensures excellent adhesive strength between the hardened coating liquid **220** and the non-metallic material (PVC sheet **230** and acrylic film **240**) contacted with the hardened coating liquid **220**. As the content of the acrylic medium is increased, the adhesive strength is enhanced. But if the content of the acrylic medium is too high, the effect of hair line is reduced. Therefore, it is preferable that the content of the acrylic medium is within an extent of 75~98% based on the whole weight.

Meanwhile, if a thickness of the coating liquid **220** is too thin, the hardened coating liquid **220** may be damaged when the transfer film **210** is removed in the third step S130. And if the thickness is too thick, the material thereof is wasted. Preferably, the thickness of the coating liquid **220** is within an extent of 3~10 μm .

In the third step, the transfer film **210** is removed after being thermally transferred onto the PVC sheet **230** so as to contact the hardened coating liquid **220** and the PVC sheet **230**. If the third step is performed, the hardened coating liquid **220** is stacked on the PVC sheet **230**, and the hair line is formed at the upper surface of the coating liquid **220**. Meanwhile, in order to ensure the adhesive strength between the PVC sheet **230** and the hardened coating liquid **220** and also prevent the hardened coating liquid **220** from being melted, it is preferable that the thermal transfer is performed at a temperature of 110~170° C.

In the fourth step S140, an acrylic film **240** is stacked on an upper surface of the hardened coating liquid **220**. The stacking of the acrylic film **240** is carried out by heat treatment.

The decoration sheet manufactured through the above-mentioned processes includes the PVC sheet **230**, the coating liquid **220** stacked on the PVC sheet **230**, and the acrylic film **240** stacked on the coating liquid **220**. The PVC sheet **230** forms the PVC layer **110**, the hardened coating liquid **220** forms the hair line printing layer **130**, and the acrylic film **240** forms the acrylic layer **150**.

It is difficult to form the hair line at a metallic material like aluminum. However, in case of using the manufacturing

5

method as described above, it is facile to form the hair line at the metallic material like aluminum.

According to the present invention, since it is possible to form the hair line at one surface of the hair line printing layer without any auxiliary layers, the decoration sheet may have a simple construction.

Further, since the hair line printing layer is formed of the mixture of the aluminum and the acryl, it is possible to provide the excellent adhesive strength between the hair line printing layer and the adjacent non-metallic layers.

Further, since the hair line printing layer ensures the weather resistance, and the acrylic layer and PVC layer also have the weather resistance, the decoration sheet has the high weather resistance.

Furthermore, according to the present invention, it is possible to facilely form the hair line at the metallic material like aluminum.

While the present invention has been described with respect to the specific embodiments, it will be apparent to those skilled in the art that various changes and modifications may be made without departing from the spirit and scope of the invention as defined in the following claims.

The invention claimed is:

1. A decoration sheet comprising:

a PVC sheet;

a hair line printing layer provided with an upper surface on which a hair line is formed and a lower surface on which the hair line is not formed, wherein the lower surface is attached to the PVC sheet; and

an acrylic film attached to the upper surface of the hair line printing layer,

6

wherein the hair line printing layer is a hardened coating liquid comprising a mixture of a liquid aluminum and an acrylic medium,

wherein the hair line printing layer has a thickness of 3-10 μm , and

wherein the acrylic medium is included in an amount of 75-98% by weight based on the total weight of the coating liquid.

2. A manufacturing method of a decoration sheet with weather resistance and hair line, which is attached to a surface of an object so as to protect the object from external environment, comprising:

forming the hair line at a surface of a transfer film;

coating a coating liquid, in which liquid aluminum and acrylic medium are mixed, on the surface of the transfer film on which the hair line is formed, and then hardening the coating liquid;

thermally transferring the transfer film onto a PVC sheet so as to contact the hardened coating liquid and the PVC sheet, and then removing the transfer film; and

stacking an acrylic film on a surface of the hardened coating liquid,

wherein, in the coating of the coating liquid on the surface of the transfer film, the coating liquid has a thickness of 3-10 μm , and

wherein the acrylic medium is included in an amount of 75-98% by weight based on the total weight of the coating liquid.

3. The manufacturing method of claim 2, wherein, in the thermally transferring of the transfer film onto a PVC sheet, the transfer film is thermally transferred onto the PVC sheet at a temperature of 110~170° C.

* * * * *