



US00922229B1

(12) **United States Patent**
Chang et al.

(10) **Patent No.:** **US 9,222,229 B1**
(45) **Date of Patent:** **Dec. 29, 2015**

- (54) **TUNABLE SANDWICH-STRUCTURED ACOUSTIC BARRIERS**
- (71) Applicant: **HRL Laboratories, LLC**, Malibu, CA (US)
- (72) Inventors: **Chia-Ming Chang**, Agoura Hills, CA (US); **Geoffrey P. McKnight**, Los Angeles, CA (US); **William Carter**, Calabasas, CA (US); **Alan J. Jacobsen**, Woodland Hills, CA (US); **Tobias A. Schaedler**, Oak Park, CA (US); **Adour V. Kabakian**, Monterey Park, CA (US)
- (73) Assignee: **HRL Laboratories, LLC**, Malibu, CA (US)
- (*) Notice: Subject to any disclaimer, the term of this patent is extended or adjusted under 35 U.S.C. 154(b) by 0 days.
- (21) Appl. No.: **14/298,858**
- (22) Filed: **Jun. 6, 2014**

Related U.S. Application Data

- (60) Provisional application No. 61/889,530, filed on Oct. 10, 2013.
- (51) **Int. Cl.**
E04B 1/82 (2006.01)
E01F 8/00 (2006.01)
- (52) **U.S. Cl.**
CPC **E01F 8/00** (2013.01)
- (58) **Field of Classification Search**
CPC E94B 1/82
USPC 181/207
See application file for complete search history.

- (56) **References Cited**
- U.S. PATENT DOCUMENTS

4,149,612 A	4/1979	Bschorr	
4,325,461 A	4/1982	Bschorr	
5,241,512 A *	8/1993	Argy et al.	367/1
5,851,626 A	12/1998	McCorry et al.	
7,249,653 B2 *	7/2007	Sheng et al.	181/290
7,263,028 B2	8/2007	Thomas et al.	
7,382,959 B1	6/2008	Jacobsen	
7,395,898 B2 *	7/2008	Yang et al.	181/286

(Continued)

- FOREIGN PATENT DOCUMENTS

GB	887535	3/1959
KR	20-1999-0025038	7/1999

- OTHER PUBLICATIONS

Geoffrey P. McKnight, et al., U.S. Appl. No. 13/645,250; Title: High bandwidth antiresonant membrane, filed Oct. 4, 2012.



(Continued)

Primary Examiner — Forrest M Phillips
(74) *Attorney, Agent, or Firm* — Christopher R. Balzan

(57) **ABSTRACT**

In one embodiment, provided is a sound attenuating barrier having a core structure between face sheets with a mass attached to at least one face sheet, and having a spatially varied stiffness distribution and/or a spatially varied density. The sound attenuating barrier may include at least one face sheet and/or core having a spatially varied stiffness distribution and/or a spatially varied mass distribution. In one embodiment, a sound attenuating barrier is provided having a core structure between face sheets with a mass structure attached to at least one face sheet, with the core/and or face sheet(s) being constructed to design an effective vibration length as well as enable a variable local stiffness and mass across the sound attenuating barrier such that the sandwich structure provides variable resonance frequency responses and broadband coverage.

31 Claims, 10 Drawing Sheets



(56)

References Cited

U.S. PATENT DOCUMENTS




7,510,052 B2 3/2009 Ayle
7,653,279 B1 1/2010 Jacobsen
8,047,329 B1 11/2011 Douglas et al.
8,066,098 B2 11/2011 Ayle
8,079,443 B2 12/2011 Keller
8,367,184 B2 2/2013 Slama et al.
8,544,597 B1* 10/2013 McEnerney 181/207
8,616,330 B1* 12/2013 McKnight et al. 181/207
8,752,667 B2* 6/2014 McKnight et al. 181/287
8,869,933 B1* 10/2014 McKnight et al. 181/286
8,960,365 B2* 2/2015 Sheng et al. 181/207
2005/0279574 A1 12/2005 Halterbeck et al.
2006/0065474 A1 3/2006 Niwa et al.
2008/0085020 A1* 4/2008 Tsai et al. 381/178

2008/0099609 A1 5/2008 Drost
2011/0064259 A1* 3/2011 Liu et al. 381/398
2013/0087407 A1* 4/2013 McKnight et al. 181/287

OTHER PUBLICATIONS

Geoffrey P. McKnight, et al., USPTO Notice of Allowance, mailed Feb. 10, 2014 for U.S. Appl. No. 13/645,250 Title: High bandwidth antiresonant membrane, filed Oct. 4, 2012.
Chia-Ming Chang, et al., U.S. Appl. No. 13/952,995; Title: Acoustic barrier support structure, filed Jul. 29, 2013.
Chia-Ming Chang, et al., U.S. Appl. No. 13/953,155; Title: Hybrid Acoustic barrier and absorber, filed Jul. 29, 2013.
Alan J. Jacobsen, et al. Shear behavior of polymer micro-scale truss structures formed from self-propagating polymer waveguides; Acta Materialia 56 (2008); pp. 1209-1218.

* cited by examiner






FIG. 2A




FIG. 2B




FIG. 2C




FIG. 3




FIG. 4




FIG. 5A




FIG. 5B




FIG. 5C




FIG. 6C




FIG. 6D




FIG. 6A










FIG. 6B






FIG. 8




FIG. 9A




FIG. 9B




FIG. 9C




FIG. 9D




FIG. 9E




FIG. 10A




FIG. 10B




FIG. 11A




FIG. 11B




FIG. 11C

TUNABLE SANDWICH-STRUCTURED ACOUSTIC BARRIERS

CROSS REFERENCE TO RELATED APPLICATION

This application claims the benefit of U.S. Provisional Application 61/889,530, entitled TUNABLE SANDWICH-STRUCTURED ACOUSTIC BARRIERS, filed Oct. 10, 2013, herein incorporated by reference in its entirety.

BACKGROUND

Conventional passive noise control approaches, such as sound absorbers or blockers, are typically either gigantic or heavy, especially for the low frequency noise control. Conventional active noise control provides another noise control option, but, its wiring and power requirement can make conventional active noise control costly, complex and hard to implement.

Further, conventional composite acoustic attenuation concepts are too heavy and bulky for certain applications. Some approaches rely on structural tension and lack stiffness control, or can be heavy if many masses are involved. Yet others have an operating frequency that is high, which makes it less effective for low-frequency operation. Another problem encountered with some conventional structures is that preciseness can be difficult to achieve as the environmental temperature changes.

The conventional noise control materials such as foams, blankets, barriers, and Helmholtz resonators rely either on homogenized material properties or dynamic behavior to reduce the noise. In the homogenized property category, the bulk materials reflect acoustic energy based on the mass law which depicts 6 dB noise reduction as doubling the frequency or surface density and the absorbent materials dissipate the energy with comparable thickness with at least one quarter of wave length. For low frequency noise control applications, the materials or the structure must be either extreme bulky and heavy to be able to provide adequate noise reduction and hence impractical for lightweight and compact requirements of modern vehicle design. As for the dynamic approaches, structural or acoustic resonators are constructed to control the noise with designated stop band frequency range; however, it is usually narrow band and less effective as frequency decreases. Further, since structural resonators with low stiffness such as membrane or thin plate often rely on structural tension to increase operation frequency which is often sensitive to environment temperature, tensioned structures resonators suffer from frequency drifting for applications with serious temperature change.

Thus, what is needed is a lightweight and compact design that is broadband and effective at low frequencies. Further, what is needed is a technology that reduces manufacturing costs and reduces environmental sensitivity to temperature or moisture.

SUMMARY

In one embodiment, the sound attenuating barrier includes a core structure between face sheets. A mass structure is attached to at least one of the face sheets. The sound attenuating barrier further includes a spatially varied stiffness distribution across the sound attenuation barrier, a spatially varied density across the sound attenuation barrier, or both.

In various embodiments, the sound attenuating barrier may include at least one face sheet having a spatially varied stiff-

ness distribution, a spatially varied mass distribution, a spatially varied stiffness distribution, a spatially varied mass distribution, or any combination of these.

In one embodiment, a sound attenuating barrier is provided having face sheets with a core structure therebetween. A mass structure is attached to at least one of the face sheets, either outside the sandwich structure or in between the face sheets. At least one of geometry or dimension being configured to provides shorter effective length of resonances such that the sandwich structure resonators provide high resonance frequency responses and broadband coverage.

DESCRIPTION OF THE DRAWINGS

These and other features, aspects, and advantages of the present invention will become better understood with reference to the following description, appended claims, and accompanying drawings where:

FIG. 1A is a perspective view of a sandwich-structured acoustic barrier.

FIG. 1B shows a side view illustrating a possible core material constructions.

FIG. 1C shows a side view illustrating a possible core material constructions.

FIG. 2A shows a beam resonance model in accordance with one possible embodiment.

FIG. 2B shows an enlarged side view of a section the beam of FIG. 2A.

FIG. 2C is a graph of the predicted response of the beam resonance model of FIG. 2A.

FIG. 3 shows a plot illustrating transmission loss simulation results of different panel configurations comparing basic variable stiffness and mass concepts.

FIG. 4 shows a graph of the insertion loss measurements for a sandwich-structured acoustic panel and its mass law prediction.

FIG. 5A shows schematic top views of various panel shapes for the sandwich-structured panel.

FIG. 5B illustrates top views of various central mass shapes.

FIG. 5C illustrates cross sectional side views of various central mass shapes.

FIGS. 6A-D are schematic top views of various embodiments of sandwich-structured panels showing potential variations in local variable stiffness and mass distributions of the sandwich-structured acoustic panels.

FIG. 7A shows a cut away side view of sandwich-structured panels illustrating distributed core strength.

FIG. 7B shows a cut away side view of sandwich-structured panels illustrating an intermediate stiffening layer within the core.

FIG. 7C shows a cut away side view of sandwich-structured panels illustrating local enhanced face sheets.

FIG. 7D shows a cut away side view of sandwich-structured panels illustrating a curved panel.

FIG. 7E shows a cut away side view of sandwich-structured panels illustrating a non-uniform thickness panel.

FIG. 7F shows a cut away side view of sandwich-structured panels illustrating portions of the core removed.

FIG. 8 is a photograph of a micro-truss structure with two distinct cellular architectures that have different properties.

FIGS. 9A-E are cut away side views depicting possible architectures that enable variable stiffness in a sandwich panel.

FIGS. 10A-B show perspective views of three-dimensional structure composed of sandwich-structured composites with variable stiffness/mass.

FIGS. 11A-C illustrate the circumferential nodal and axial nodal patterns for a cylindrical sandwich structured acoustic barrier.

DESCRIPTION

In various embodiments, an architected acoustic sandwich-structured barrier is a panel composed of a core structure and face sheets with variable local stiffness and density, which blocks acoustic energy. Various embodiments use variable stiffness and mass distribution across the sandwiched structure to construct a tunable and broadband anti-resonance sound barrier.

Besides benefiting from sandwich panel configurations, high bending stiffness can be achieved without mass penalty and structural tension, which enables compact, lightweight, noise and vibration control with high temperature tolerance in harsh chemical and/or humidity environment. The nature of high bending stiffness makes various embodiments a good candidate for multifunctional noise control, providing both acoustic isolation and structural support or mechanical loads. It is conceivable that the concept can be integrated into generic panel construction approaches to yield the added benefit of targeted noise control to applications that currently use sandwich panels.

In various embodiments, it is possible to create a lightweight, compact, and scalable noise blocking panel with high temperature tolerance and robustness in harsh environment. By designing core materials such as honeycomb, or truss architecture, and face sheets with a variable stiffness and density distribution, various embodiments of the sandwich panel may provide a compact, lightweight noise control treatment which is not only scalable, easy manufacture, and temperature insensitive, but can be constructed into a protecting case for mechanical and/or electrical components.

Thus, in various embodiments it is possible to use compact and lightweight sandwiched core structure with variable stiffness and mass design to provide noise control at low or mid audible frequency (30-1000 Hz) which is challenging for conventional noise control. The face sheet construction and the non-tension design may provide high temperature tolerance and good robustness in harsh environments.

In accordance with some embodiments, a non-tension design is possible, as well as a tailored variable stiffness or mass. Furthermore, some embodiments may provide a compact, lightweight, robust architected acoustic blocking panel with high noise reduction at ultra-low frequencies and good temperature tolerance for noise control. Various embodiments can provide a passive noise control solution with advantages of low weight, compactness, high noise reduction, and environmental robustness.

Various embodiments may utilize scalable, flexible, and conformal truss/lattice fabrication technique, such as for example microtruss, to benefit lightweight acoustic barriers technology. Various embodiments may provide noise control or acoustic blocking in vehicles, such as automobiles and aircraft, or in commercial products that contain noisy components (motors, pumps, compressors, transmissions, transformers, ducts, etc.), including appliances, grinders, blenders, microwave ovens, sump pumps, etc.

FIG. 1A is perspective view of a sandwich-structured acoustic barrier **100**. FIGS. 1B and 1C are side views **160** and **170**, respectively, illustrating two of many possible core material constructions. FIGS. 1A-C illustrate sandwich-structured acoustic composites **100**, **160**, and **170** with variable stiffness/mass which can isolate noise for low frequency applications. The sandwiched face sheets and core structure

with designated stiffness and mass distribution creates an effective acoustic barrier to block noise based on the concepts of negative mass. The sandwich structure behaves as a vibration dipole with a nearly zero total volume displacement across the structure, and results in a weak acoustic radiation in the anti-resonance frequency range between principal resonances.

While previous membrane-type resonators can provide lightweight solutions for noise control, the challenges were found for some applications such as narrow band coverage at ultra-low frequencies (frequencies less than about 500 Hz) and damage or frequency shifting in harsh environment (high temperature variation). For sandwich-structured resonators, various embodiments take advantage of the system structure and the variable local stiffness and mass to efficiently tailor the vibration modal in large scale. In addition, the nature of high bending stiffness (no tension needed) with lightweight benefit and flexible manufacturing of sandwiched structure makes this sandwich-structured acoustic panel suitable to ultra-low frequency with large size design and harsh environment applications which compensate the current membrane-type designs.

The simplified illustration shown in FIG. 1A shows a sandwich-structured acoustic panel **100** with variable stiffness/mass, illustrated in areas **123**, **125**, and **127**, capable of blocking incident sound waves, illustrated by arrow **105**. The sandwich-structured composite **100** has face sheets **110** and **130**, a central mass **112**, and a core material/structure **120** to create vibration modes with low acoustic radiation **106** at designated noise frequencies. The central mass **112** and the sandwiched structure **150** with bending stiffness create a multiple degree of freedom mass-spring resonating system which blocks acoustic energy **105** at its anti-resonance frequencies, particularly between the first two odd principal resonances. FIGS. 1B and 1C show without limitation, some possible core material/structure configurations including honeycomb and truss/lattice structures **165** and **175** with variable stiffness/mass distribution throughout the panel. In addition to the honeycomb, foam, either open cell or closed cell, may be used for the core material. In addition, other cellular constructs, such as a box pattern, can be used. Acoustic performance may be enhanced with the open core materials (microlattice or honeycomb) through the introduction of porous absorption, either through fibrous batting or mats, or a light, open cellular material such as an open celled foam.

FIGS. 2A-2C show the sandwiched structure layout and parametric estimation of non-tensioned system's resonance frequencies. A simplified sandwich beam **215** is shown in FIG. 2A. The beam **215** consists of uniform layers of face sheets **210** and **230** which are perfectly attached to the rigid core structure **220**. FIG. 2B shows an enlarged section **235** of the beam **215** of FIG. 2A. In the equation,

$$f_{res} \propto \frac{1}{L^2} \left(\frac{EI}{m} \right)^{0.5}$$

where

$$I = \frac{2b}{3} (d_{out}^3 - d_m^3)$$

such that

$$f_{res} \propto \frac{1}{L^2} \left(\frac{EI}{m} \right)^{0.5} \propto \frac{1}{L^{2.5}} \left(\frac{E(d_{out}^2 + d_{out}d_{in} + d_{in}^2)}{\rho} \right)^{0.5}$$

the resonance frequency f_{res} is dominated by beam length L , the core depth d_{in} , and the thickness of face sheets, d_{out} - d_{in} . Basically, the first resonance increases with higher core and face sheet thickness, and decreases with larger panel size. Compared to a single sheet with the same weight, it is known that the sandwich-structured composites have significantly higher resonance frequencies due to the high bending stiffness. For resonator-type acoustic barriers, it is important for the structure to have high bending stiffness since a larger planar dimension or thinner panel can be implemented at the same target frequency without using structural tension.

FIG. 2C is a graph 250 of the predicted response of the laminated sandwich beam shown in FIG. 2A. The graph 250 shows a comparison of 1st and 3rd resonance frequencies as function of core thickness of a fixed-fixed beam 215. The solid lines 252 and 254 represent results of a sandwiched core composite beam with 0.4 mm thick Al face sheets. The dashed lines 251 and 253 represent the results of a solid Al beam. While the frequency and band width between 1st and 3rd modes increase as the beam thickness rises, the sandwiched core beam 215 has higher resonance frequencies and larger band width between 1st and 3rd modes.

In FIG. 2C, the resonance frequencies are compared between the sandwiched core composite and a solid beam with the same beam thickness. Although the solid beam definitely has higher bending stiffness than sandwiched core composite beam, the solid beam's weight counteracts its higher bending stiffness and makes the resonance frequencies even lower than the sandwiched core composite beam. With disadvantages of lower resonances and heavy weight; therefore, the solid beam becomes impractical for lightweight noise control applications. This lightweight and high bending stiffness characteristic makes the sandwich-structured panel a good acoustic barrier with scalable dimension at target frequencies of hundred hertz regime without using structural tension.

FIG. 3 shows a plot 300 illustrating transmission loss simulation results of different panel configurations comparing basic variable stiffness and mass concepts. The panel size is 9.5 inch×9.5 inch and the 5 mm thick core structure is configured into concentric circles with spacing of 0.1 inch and modulus of 30 GPa. Represented in the graph 300 of FIG. 3 curve 302 is of a single 35.4 mils Al sheet embodiment; curve 304 is of a two separate 17.7 mils Al sheets embodiment; curve 306 is of a sandwiched core panel with two 17.7 mils thick Al face sheets and 40 g central mass embodiment; curve 308 is of a sandwiched core panel with two 17.7 mils thick Al face sheets and 100 g central mass embodiment.

FIG. 3 shows the transmission loss simulation results in the frequency spectrum of four examples to understand sandwiched composite's acoustic performance. Curve 302 shows the transmission loss of a single 0.9 mm thick Al sheet. In this curve, the 1st and 3rd resonances are at 60 Hz and 250 Hz while the anti-resonance peaks at 150 Hz with medium transmission loss and narrow bandwidth. If the 35.4 mils thick sheet is split into two 17.7 mils thick sheets without a core material, as shown in the curve 304, both resonances decrease and low transmission loss and narrower bandwidth is observed. However, as shown in the curve 306, a significant increase of resonance frequencies, transmission loss ampli-

tude, and bandwidth can be obtained when a lightweight core material is sandwiched between 17.7 mils face sheets with a 40 g central tile mass. This result theoretically indicates that the concept of non-tensioned sandwich-structured acoustic barriers possess high bending stiffness, lightweight/compact advantages and good noise control capability. Adding additional mass to the center, as described and shown for curve 308, pushes the 1st resonance downward while having similar 3rd resonance broadens the effective bandwidth.

FIG. 4 shows a graph 400 of insertion loss measurements for a sandwich-structured acoustic panel (10"×10"×0.16" Al honeycomb panel with 36 gram and 72 gram panel central mass; stiffness not optimized). Compared insertion loss measurement of 36 gram attached mass panel with its mass law prediction curve 402 (dashed), the panel has better insertion loss with 400 Hz band width centered at 550 Hz and 20 dB noise reduction at 500 Hz than the mass law prediction.

The 10 inch×10 inch×0.16 inch sandwiched panel comprises of two identical 15 mils thick Al face sheets, a 0.125 inch thick Al honeycomb, and a 36 gram or 72 gram central mass. The bending stiffness and mass distribution is uniform throughout the panel in this sample and different weight was attached at panel center to study the panel dynamics and related acoustic performance. The 36 g curve shows a dip around 400 Hz and peaks at 510 Hz with a gradual decrease until reaches another dip at 1100 Hz. The dips at 400 Hz and 1100 Hz are the 1st (0,1) and 3rd (0,3) resonances where the acoustic energy transmits efficiently through the panel. At the curve peak around 510 Hz, the insertion loss reaches 45 dB which is more than 20 dB higher compared to the mass law prediction curve 402 (dashed curve—mass law with 36 grams added mass). By adding more central weight to the panel, the 72 grams curve shows a downward 1st resonance shifting and steady 3rd resonance which results in broader band width and low frequency noise reduction. This result shows clear evidence how variable mass approach tunes the panel acoustic performance. Since traditional resonators always have narrow band coverage at low frequency noise control, the wide band coverage in this example provides a promising solution for low frequency noise control. With other available design parameters such as panel size, central mass arrangement, global/local core stiffness, global/local face sheet thickness, and curvature of panel, a lightweight, compact, robust, and non-tensioned sandwich-structured acoustic panel can be designed for specific noise control applications. The following paragraphs detail the design parameter trade space.

FIG. 5A shows different possible shapes of sandwich-structured acoustic panels and central mass configurations. FIG. 5A shows a square shape sandwich panel 500 with a central mass 512. The central mass 512 design may include any of the shapes, such as but not limited to circular 512a, annular 512b, bulls eye 512c (combined circular and annular), square 512d, rectangular 512e, hexagonal 512f, elliptical 512g, or star 512h, such as illustrated in FIG. 5B, and any of the cross sections, such as but not limited to rectangular 512i, "T" shape 512j, "I" shape 512k, hollow rectangular 512m, triangular 512n, as shown in FIG. 5C. The mass 512 attachment may be, but is not necessarily on the panel surface; it could be integrated inside the panel with the core materials/structures to retain a thin profile and for aesthetics. The number of masses is also not limited to a single unit; it could be a mass array on designated area.

There are two main purposes to use different shaped weights: 1. Define effective panel bending length or compensate panel's irregular shape to control mode shapes and obtain required acoustic performance. 2. Multiple weights for different target frequencies such as concentric circles. As for the

cross section of mass, shapes such as I, T, or hollowed geometries can be selected to design thin or slender central weight while maintain rigidity.

In the mass-spring system, the mass/weight decreases the 1st resonance but has little influence on 2nd resonance. The size of the mass determines the effective panel length for 1st & 3rd mode shape. A larger mass size occupies more panel area and shortens the effective panel length for 1st and 3rd mode resonances. This slightly raises the 1st mode resonance frequency and significantly increases the 3rd mode resonance frequency which broadens the noise reduction bandwidth.

In FIG. 5A, also shown are schematic top views of other possible embodiments of the panel shape. Shown are circular 551, triangular 552, hexagonal 553, rectangular 554, and trapezoidal 555 panel shapes.

Embodiments are not limited to these shapes or cross sections, other shapes or cross sections are possible. The selection of panel shape depends on the geometrical shape of different applications.

The central mass structure may be attached to at least one of the face sheets, either outside the sandwich structure, or in between the face sheets, or both. At least one of the geometry or dimension being configured to provide shorter effective length of resonances such that the sandwich structure resonators provide high resonance frequency responses and broadband coverage.

FIGS. 6A-6D are a schematic top views showing potential variations in local variable stiffness and mass distributions of sandwich-structured acoustic panels. As discussed in previous sections, the sandwiched core structure has significantly higher resonances than a beam with the same weight or the same thickness due to its high bending stiffness/weight ratio. However, as a resonator-type acoustic barrier, it is important to control other individual modes for wider noise reduction bandwidth and higher transmission loss magnitude. As such, various embodiments make use of planar mode control through the targeted application and design of local stiffness and mass variations.

In FIG. 6A, the top view schematic shows the basic concept of local property design to control the 1st and 3rd vibration modes. There are three areas: weighted area 612a, stiffened areas 625a and 627a, and reduced mass areas 624a and 626a; and each can be achieved by designing non-uniform core materials and tailored stiffness face sheet layouts. Previous studies on membranes indicated that adding central weights could decrease the 1st mode without changing the 3rd mode frequency which broadens the bandwidth between these two modes. Further, larger weighted area will shorten the effective panel bending length of 3rd mode resonance, which correspondingly raises the 3rd mode resonance frequency.

In practice, high bending stiffness of sandwich panels relies on the interaction of both a rigid core structure and axially stiff face sheets to carry the applied loads. A soft core material experiences a shear deformation, particularly at the nodes of the panel's vibration modes. By enhancing core's shear strength with high strength face sheets in node areas 625a and 627a as shown in the FIG. 6A, the 3rd mode resonance can be increased which broadens the bandwidth. FIG. 6A shows a face sheet 610a stiffened in concentric annular ring shaped areas 625a and 627a.

Finally, reducing the weight or mass at the anti-node of the mode as shown in FIG. 6A by reduced mass areas 624a and 626a, the 3rd mode resonance frequency can be increased. This local stiffness and mass distribution will vary depending on the panel shape and configuration, such as FIG. 6B for a rectangular panel with an elliptical weighted area 612b, elliptical stiffened areas 625b and 627b, and elliptical reduced

mass areas 624b and 626b; but, the essential mechanism and targeted vibration behavior remains the same. In FIG. 6C and (d) are two local stiffness and mass designs which will raise 3rd resonance and serve to broaden the effective bandwidth of acoustic attenuation. Shown in FIG. 6C are weighted area 612c, generally straight segment shaped stiffened areas 625c and 627c, and reduced mass areas 624c. Shown in FIG. 6D are weighted area 612d, outwardly extending curved shaped stiffened areas 625d and 627d, and reduced mass areas 624d.

FIGS. 7A-7E show cut away side views of sandwich-structured panels with a variable stiffness and its configurations. Conventionally, the bending stiffness (as resonant frequencies) of a sandwich panel is altered through changing the core thickness. In FIGS. 7A-7E, shown are embodiments that can tune the stiffness spatially to better control the vibration modes and subsequently the acoustic radiation. FIG. 7A is an embodiment 700a that shows local stiffness control through core structure 750a design. A central mass 712a is attached to the face sheets 710a and 730c. A core 750a with locally strengthened core portions 755a to provide distributed core strength. FIG. 7B is the embodiment 700b having an intermediate stiffening layer 751b, which enhances the shear modulus of core materials 750b. As mentioned previously, the shear modulus determines the bending stiffness of the panel. This approach improves the shear modulus and increases the global/local stiffness which could increase resonance frequency of all resonances or specific mode to create broad bandwidth. FIG. 7C is an embodiment 700c that shows the local stiffness control of face sheets 710c and 730c. The face sheets 710c and 730c are locally enhanced by enhanced areas 711c and 713c. The sheet 710c or 730c thickness and the locally enhanced techniques, such as incorporated fiber composites, can be designed to tune the local stiffness. FIG. 7D is an embodiment 700d that shows the curved panel design, which addresses the applications with curved profiles. The curved structures also exhibit higher resonances than straight plates which benefits the compact panel design and higher frequency applications. FIG. 7E discloses the non-uniform panel sandwiched panel design 700e. By varying the local panel 700e thickness with sandwiched core materials 750e, the local stiffness can be significantly changed. The panel 700e thickness is determined by face sheet 710e and 730e profiles, which can be molded or embossed into the desired geometry. In FIG. 7E, the face sheets are non-planar with opposing face sheets 710e and 730e are symmetrical with respect to a plane extending between the face sheets 710e and 730e.

As depicted in FIG. 7A, the variable core structure 750a can be fabricated, for example, using the truss/lattice process as disclosed in U.S. Pat. No. 7,382,959, entitled OPTICALLY ORIENTED THREE-DIMENSIONAL POLYMER MICROSTRUCTURES by Alan J. Jacobsen, issued Jun. 3, 2008, herein incorporated by reference in its entirety. With this scalable process, different designs such as truss orientation, size, and density are possible within a single, continuous core material, the shear modulus can be locally varied by tuning the cellular architecture of the micro-truss core as described below.

The shear modulus of a micro-truss core material with octahedral-type architecture can be estimated using the following equation:

$$G \approx \frac{E}{8} \left(\frac{\rho}{\rho_s} \right) \sin^2 2\theta$$

where (ρ/ρ_s) is the relative density of the structure defined by,

$$\frac{\rho}{\rho_s} = \frac{2\pi r^2}{P \cos^2 \theta \sin \theta}$$

and the variables r , l , and θ represent the individual truss member radius, length, and angle, respectively. The radius (r) and the length (l) can be individually tuned within the truss to locally vary the shear modulus, and hence the panel stiffness. FIG. 8 is an example of a micro-truss structure with two different architectures (and local shear moduli) in a single continuous material. As shown in FIG. 8, one embodiment the microtruss structure can be formed of a plurality of ordered polymer microtruss members integrally connected at nodes. The microtruss members extend from a node in different directions, typically extending from a node with a non-perpendicular angle with at least one other microtruss member. Shown in FIG. 8, the microtruss members near a center portion 850c of the lattice are more closely spaced than the peripheral microtruss members 850p surrounding the central portion 850c, so which form a less dense lattice structure 850p.

Another approach to generate local areas of core stiffness is to machine or etch the core such that during sandwich panel fabrication, areas of the core are not contacted or adhered to the facesheets. FIG. 7F shows a cut away side view of sandwich-structured panel 700f illustrating a core 750f that has portions 755f₁, 755f₂, 755f₃, and 755f₄ removed, such as by etching, machining, or the like. The locally removed portions 755f₁, 755f₂, 755f₃, and 755f₄ will reduce the load transfer locally and affect the stiffness and resonant frequencies of particular modes.

Further, additive manufacturing methods including selective laser sintering, selective electron beam melting and stereo lithography, as well as the truss/lattice process disclosed in the above referenced U.S. Pat. No. 7,382,959 can be used to create a variety of structures with variable stiffness. Location specific stiffness can be achieved by adding reinforcements in certain locations, for example additional diagonal connections 975a between the two face sheets 910a and 930a results in higher shear stiffness (FIG. 9A). FIGS. 9A-9E are cut away side views depicting possible architectures that enable variable stiffness in a sandwich panel.

As described in FIG. 7B, shear modulus determines panel's bending stiffness, i.e. higher bending stiffness requires high shear modulus of the core material/structure. With the configurations shown in FIGS. 9B-9E, the shear stiffness can be varied independent of the mass by varying the angles of the interconnections between the two face sheets. As shown in FIG. 9B, an angle closer to 45° (for trusses 975b) results in higher shear stiffness than an angle closer to 90° (for trusses 976b). Another way to increase shear stiffness is to add horizontal reinforcements 975c (FIG. 9C). As shown in FIG. 9C, this can be achieved by inserting machined sheets 975c when assembling the sandwich panel from 2 cores and 2 face sheets. With this approach, ring shaped or other sheets 975c can be inserted as shown in FIG. 9C. Different patterns of different materials 975d could also be employed where stiff materials 975d_s could be used to enhance stiffness and compliant materials 975d_c (polymers, rubber) could be used to lower stiffness (FIG. 9D). FIG. 9E shows a preferred embodiment of a micro-truss half layer structure 900e that provides excellent shear stiffness, which can be varied easily by altering the diameter of trusses 976e and 977e locally.

Based on the flexible core material/structure control, such as the microtruss structures disclosed in the above referenced U.S. Pat. No. 7,382,959, a local stiffness and mass can be modified to address various applications. All embodiments described above can be used alone or combined to achieve the best performance for specific requirements.

FIG. 10A-10B show perspective views of the three-dimensional structures or enclosures 1000a and 1000b having sandwich-structured acoustic barriers. The enclosures 1000a and 1000b are typically hollow enclosure structures that may be partial or full enclosures 1000a and 1000b. The rectangular enclosure 1000a has interior face sheets (not shown) and exterior face sheet(s) 1030a, with a core (not shown) between the interior and exterior face sheets. The cylindrical enclosure 1000b has an interior face sheet 1010b, and an exterior face sheet 1030a, with a core 1050b between the interior and exterior face sheets 1010a and 1030b. Mechanical and electrical equipment can emit objectionable tones due to operation that must be shielded and dissipated to isolate the equipment from its environment. Depending on the enclosed sound emitting components/machines and principal emission frequencies, the panel or panels can be designed/configured according to the dimension and noise control requirements.

As shown in FIG. 10B, the sandwiched panel 1000b can be fabricated into a cylindrical configuration with a distributed weight array. With the circumferential nodal and axial nodal patterns 1100b and 1100a, respectively, shown in FIGS. 11A-11C, the cylindrical structure can be designed into lightweight acoustic barriers for different applications.

In addition, there are several material options to construct the tunable sandwich-structured acoustic barriers. The resonator can be transparent if transparent materials such as glass or transparent plastic are used. In the enclosure with heat-generated component, thermal conductivity of the face sheets and core materials is important to dissipate the extra heat. When using a microtruss core, it may be advantageous to combine the sandwich panel treatment with a force flow fluid heat extraction turning the acoustic treatment into a cold plate heat removal system. For the thermal insulation required applications, such as commercial aircraft cabin or helicopter fuselage, heat insulating materials can be used for face sheets and core structures and coated with reflected layer to reflect back the heat energy. Because of the high stiffness nature, the sandwiched core panel can be used to build blast protection case.

FIGS. 11A-11C illustrate possible circumferential nodal and axial nodal patterns 1100b and 1100a, respectively. FIG. 11C shows a perspective view of a cylindrical sandwich structured acoustic barrier with variable stiffness showing the circumferential and axial nodes 1100b and 1100a, respectively. FIG. 11A illustrates the circumferential node patterns 1100a for $n=0$ to $n=4$. FIG. 11C illustrates the circumferential node patterns 1100b for $m=0$ to $m=3$.

In various embodiments, a sound attenuating panel may be created using a sandwich panel construction with spatially varying distributions of stiffness and concentrated masses.

In some embodiments, the face sheets may be spatially tailored to control its stiffness and create a single pair of interacting vibrations modes. In some embodiments, the face sheets may be formed of flat sheets, curved sheets, or conformal sheets. In some embodiments, the face sheets may be formed of sheets with varying thickness to tailor local stiffness and mass. In some embodiments, the face sheets may be formed of sheets with local enhanced woven and knitting fiber composite. In some embodiments, the face sheets are made of metal, polymer, ceramic, fiber-enhanced composite and paper based materials.

In some embodiments, the core material/structure may be spatially tailored to control its stiffness and create a single pair of interacting vibrations modes. In some embodiments, the spatially tailored core is formed of a microlattice layer. In some embodiments, the spatially tailored core is formed of a honeycomb or other repeating cellular structure. In some embodiments, the shear modulus of the core material is tailored and enhanced to improve panel bending stiffness with a central stiffening layer. In some embodiments, the spatially tailored core is made of metal, polymer, ceramic, fiber-enhanced composite, and paper based materials. In some embodiments, the core material is composed of a closed or open cell cellular material such as foam that is either uniform or altered in stiffness or density through the assembly of pieces of different density foams. In some embodiments, the micro-lattice or honeycomb core is enhanced with the addition of a fabric or porous absorber to dampen cavity mode acoustic energy. In some embodiments, the micro-lattice or honeycomb core is enhanced with the structure absorber to dissipate acoustic energy. In some embodiments, the honeycomb core is machined so that regions of the core do not touch and transfer load into the face sheet

In some embodiments, the panel shape comprises at least one of rectangular, square, triangle, polygons, circular, or irregular. The attached mass may be external, or integrated into the core material. The attached mass may comprise circular, oval, rectangular shapes, solid or hollow 3D shapes, or have a stepped profile to extend the free length of the sandwich panel.

Various embodiments, of the tailored stiffness panel may be used to create an enclosure to contain emission from equipment or machinery. For example, various embodiments may be formed into a cylindrical shape to contain emission from equipment or machinery.

It is also possible, in accordance with the teachings above, to also have a variable local damping across the sandwich-structured acoustic panel. For example, the core material itself may provide some damping for the sandwich-structure panel. It is possible to use different materials in the core to vary the damping across the sandwich-structured acoustic panel.

In one embodiment, a sound attenuating barrier is provided having a core structure between face sheets with a mass structure attached to at least one face sheet, with the core/and or face sheet(s) being constructed to design an effective vibration length, as well as enable a variable local stiffness and mass across the sound attenuating barrier such that the sandwich structure attenuators provide variable resonance frequency responses and broadband coverage.

In general, a heavier central mass weight provides decreased 1st resonance. Further, a larger central mass provides some increased 1st mode resonance, but it especially 3rd mode resonance. A thicker core provides an increase all frequencies. Local core thickness, core strength, facesheets, and cutaways affect the local stiffness, while local core density and face sheets affect the local density.

The mass geometry and size is one of the key points to increase the resonance frequencies and bandwidth. For example, the central mass with larger diameter increases resonance frequencies, which are important to targeting certain application frequencies and broadening the bandwidth for panels with a larger dimensions.

As used herein a "barrier" can partially or completely attenuate sound.

It is worthy to note that any reference to "one embodiment/implementation" or "an embodiment/implementation" means that a particular feature, structure, action, or charac-

teristic described in connection with the embodiment/implementation may be included in an embodiment/implementation, if desired. The appearances of the phrase "in one embodiment/implementation" in various places in the specification are not necessarily all referring to the same embodiment/implementation.

The illustrations and examples provided herein are for explanatory purposes and are not intended to limit the scope of the appended claims. This disclosure is to be considered an exemplification of the principles of the invention and is not intended to limit the spirit and scope of the invention and/or claims of the embodiment illustrated.

Those skilled in the art will make modifications to the invention for particular applications of the invention.

The discussion included in this patent is intended to serve as a basic description. The reader should be aware that the specific discussion may not explicitly describe all embodiments possible and alternatives are implicit. Also, this discussion may not fully explain the generic nature of the invention and may not explicitly show how each feature or member can actually be representative or equivalent members. Again, these are implicitly included in this disclosure. Where the invention is described in device-oriented terminology, each member of the device implicitly performs a function. It should also be understood that a variety of changes may be made without departing from the essence of the invention. Such changes are also implicitly included in the description. These changes still fall within the scope of this invention.

Further, each of the various members of the invention and claims may also be achieved in a variety of manners. This disclosure should be understood to encompass each such variation, be it a variation of any apparatus embodiment, a method embodiment, or even merely a variation of any member of these. Particularly, it should be understood that as the disclosure relates to members of the invention, the words for each member may be expressed by equivalent apparatus terms even if only the function or result is the same. Such equivalent, broader, or even more generic terms should be considered to be encompassed in the description of each member or action. Such terms can be substituted where desired to make explicit the implicitly broad coverage to which this invention is entitled. It should be understood that all actions may be expressed as a means for taking that action or as a member which causes that action. Similarly, each physical member disclosed should be understood to encompass a disclosure of the action which that physical member facilitates. Such changes and alternative terms are to be understood to be explicitly included in the description.

While the present invention has been described in connection with certain exemplary embodiments, it is to be understood that the invention is not limited to the disclosed embodiments; on the contrary, it is intended to cover various modifications and equivalent arrangements included within the spirit and scope of the appended claims, and equivalents thereof.

What is claimed is:

1. A sound attenuating barrier comprising:

- a) face sheets;
- b) a core structure between the face sheets;
- c) a mass structure attached to at least one of the face sheets; and
- d) the sound attenuating barrier further comprising at least one of: (1) a spatially varied stiffness distribution; or (2) a spatially varied density across the sound attenuation barrier.

2. The sound attenuating barrier of claim 1, wherein at least one face sheet comprises a non-planar face sheet.

3. The sound attenuating barrier of claim 1, wherein at least one of the face sheets is a curved face sheet.

4. The sound attenuating barrier of claim 1, wherein the sound attenuating barrier comprises a three dimensional enclosure.

5. The sound attenuating barrier of claim 1, wherein the at least one of: (a) the variable local stiffness across the sound attenuating barrier; or (b) the variable density across the sound attenuating barrier is configured such that a single pair of interacting vibration modes are created in response to incident sound within a desired frequency range.

6. The sound attenuating barrier of claim 1, wherein at least one face sheet comprises: (a) a spatially varied stiffness distribution; or (b) a spatially varied mass distribution.

7. The sound attenuating barrier of claim 6, wherein the at least one face sheet comprises stiffed areas configured so as to broaden a bandwidth by increasing the third mode resonance.

8. The sound attenuating barrier of claim 7, wherein the at least one face sheet further comprises at least one reduced mass area configured so as to broaden a bandwidth by increasing the third mode resonance.

9. The sound attenuating barrier of claim 6, wherein the at least one face sheet comprises reduced mass areas configured so as to broaden a bandwidth by increasing the third mode resonance.

10. The sound attenuating barrier of claim 6, wherein the at least one face sheet comprises a plurality of generally linear stiffener regions.

11. The sound attenuating barrier of claim 6, wherein the at least one face sheet comprises a plurality of generally curved stiffener regions.

12. The sound attenuating barrier of claim 6, wherein at least one face sheets comprises at least one stiffened annular region.

13. The sound attenuating barrier of claim 12, wherein the at least one stiffened annular region is ellipse shaped.

14. The sound attenuating barrier of claim 12, wherein the at least one face sheet further comprises at least one reduced mass annular region.

15. The sound attenuating barrier of claim 6, wherein the at least one face sheet comprises at least one reduced mass annular region.

16. The sound attenuating barrier of claim 6, wherein the core structure comprises at least one of: (a) a spatially varied stiffness distribution; or (b) a spatially varied mass distribution.

17. The sound attenuating barrier of claim 1, wherein the core structure comprises at least one of: (a) a spatially varied stiffness distribution; or (b) a spatially varied mass distribution.

18. The sound attenuating barrier of claim 17, wherein the core structure is configured so as to broaden a bandwidth by increasing the third mode resonance of the sound attenuating barrier.

19. The sound attenuating barrier of claim 17, wherein the core structure comprises at least a portion having greater stiffness than an adjacent portion of the core structure.

20. The sound attenuating barrier of claim 17, wherein the core structure comprises a variable density across the sound attenuating barrier.

21. The sound attenuating barrier of claim 17, wherein the core structure comprises an ordered three dimensional microtruss.

22. The sound attenuating barrier of claim 17, wherein at least a portion of the core structure comprises cross linking members.

23. The sound attenuating barrier of claim 17, further comprising a stiffening sheet within the core structure.

24. The sound attenuating barrier of claim 17, further comprising a stiffening layer within the core structure.

25. The sound attenuating barrier of claim 17 further comprising a layer comprising stiff materials and compliant materials within the core structure.

26. The sound attenuating barrier of claim 17, wherein the core structure comprises support structures extending between the face sheets and having a distribution of different angles across the core structure with respect to the face sheets.

27. The sound attenuating barrier of claim 17, wherein the core structure is attached to the face sheets.

28. The sound attenuating barrier of claim 17, wherein the core structure abuts the face sheets and comprises at least a portion abutting the core structure but not attached to a face sheet.

29. The sound attenuating barrier of claim 17, wherein the core structure comprises a portion adjacent to but recessed from a face sheet.

30. The sound attenuating barrier of claim 17, wherein the core structure comprises a non-uniform thickness.

31. The sound attenuating barrier of claim 30, wherein the face sheets both comprise a non-planar face sheet, and wherein opposing face sheets are symmetrical with respect to a plane extending between the non-planar face sheets.

* * * * *