

(12) **United States Patent**  
**Horng et al.**

(10) **Patent No.:** **US 9,305,864 B2**  
(45) **Date of Patent:** **Apr. 5, 2016**

(54) **THROUGH SILICON VIA (TSV) ISOLATION STRUCTURES FOR NOISE REDUCTION IN 3D INTEGRATED CIRCUIT**

USPC ..... 257/276, 621, 698, E23.067, 341, 401, 257/774; 438/667  
See application file for complete search history.

(71) Applicant: **TAIWAN SEMICONDUCTOR MANUFACTURING CO., LTD.**, Hsin-Chu (TW)

(56) **References Cited**

(72) Inventors: **Jaw-Juinn Horng**, Hsinchu (TW); **Chia-Lin Yu**, Sigang Township (TW); **Chung-Hui Chen**, HsinChu (TW); **Der-Chyang Yeh**, Hsin-Chu (TW); **Yung-Chow Peng**, Hsinchu (TW)

U.S. PATENT DOCUMENTS

5,391,917 A 2/1995 Gilmour et al.  
5,510,298 A 4/1996 Redwine  
5,767,001 A 6/1998 Bertagnolli et al.  
5,998,292 A 12/1999 Black et al.  
6,107,149 A 8/2000 Wu et al.

(Continued)

(73) Assignee: **Taiwan Semiconductor Manufacturing Co., Ltd.**, Hsin-Chu (TW)

OTHER PUBLICATIONS

(\* ) Notice: Subject to any disclaimer, the term of this patent is extended or adjusted under 35 U.S.C. 154(b) by 156 days.

Cho, J. et al., "Through Silicon Via (TSV) Shielding Structures", Electrical Performance of Electronic Packaging and Systems (EPEPS), 2010 IEEE 19th Conference, pp. 269-272.

(21) Appl. No.: **14/024,925**

*Primary Examiner* — Julio J Maldonado

(22) Filed: **Sep. 12, 2013**

*Assistant Examiner* — Cory Eskridge

(65) **Prior Publication Data**

US 2014/0008817 A1 Jan. 9, 2014

(74) *Attorney, Agent, or Firm* — Duane Morris LLP

**Related U.S. Application Data**

(63) Continuation of application No. 13/324,405, filed on Dec. 13, 2011, now Pat. No. 8,546,953.

(57) **ABSTRACT**


(51) **Int. Cl.**  
**H01L 23/48** (2006.01)

Through silicon via (TSV) isolation structures are provided and suppress electrical noise such as may be propagated through a semiconductor substrate when caused by a signal carrying active TSV such as used in 3D integrated circuit packaging. The isolation TSV structures are surrounded by an oxide liner and surrounding dopant impurity regions. The surrounding dopant impurity regions may be P-type dopant impurity regions that are coupled to ground or N-type dopant impurity regions that may advantageously be coupled to  $V_{DD}$ . The TSV isolation structure is advantageously disposed between an active, signal carrying TSV and active semiconductor devices and the TSV isolation structures may be formed in an array that isolates an active, signal carrying TSV structure from active semiconductor devices.

(52) **U.S. Cl.**  
CPC ..... **H01L 23/481** (2013.01); **H01L 2924/0002** (2013.01)

(58) **Field of Classification Search**  
CPC ..... H01L 23/481; H01L 2225/06541; H01L 23/49827; H01L 23/5384; H01L 21/486; H01L 21/76831; H01L 2225/06544; H01L 2223/6622

**20 Claims, 6 Drawing Sheets**



(56)

References Cited

U.S. PATENT DOCUMENTS

6,184,060	B1	2/2001	Siniaguine	7,060,601	B2	6/2006	Savastiouk et al.	
6,322,903	B1	11/2001	Siniaguine et al.	7,071,546	B2	7/2006	Fey et al.	
6,448,168	B1	9/2002	Rao et al.	7,111,149	B2	9/2006	Eilert	
6,465,892	B1	10/2002	Suga	7,122,912	B2	10/2006	Matsui	
6,472,293	B1	10/2002	Suga	7,157,787	B2	1/2007	Kim et al.	
6,538,333	B2	3/2003	Kong	7,193,308	B2	3/2007	Matsui	
6,563,181	B1	5/2003	Du et al.	7,262,495	B2	8/2007	Chen et al.	
6,599,778	B2	7/2003	Pogge et al.	7,297,574	B2	11/2007	Thomas et al.	
6,639,303	B2	10/2003	Siniaguine	7,335,972	B2	2/2008	Chanchani	
6,664,129	B2	12/2003	Siniaguine	7,355,273	B2	4/2008	Jackson et al.	
6,693,361	B1	2/2004	Siniaguine et al.	7,427,803	B2	9/2008	Chao et al.	
6,740,582	B2	5/2004	Siniaguine	7,701,057	B1 *	4/2010	Rahman et al. ....	257/750
6,800,930	B2	10/2004	Jackson et al.	8,546,953	B2 *	10/2013	Horng et al. ....	257/774
6,841,883	B1	1/2005	Farnworth et al.	2009/0134500	A1	5/2009	Kuo	
6,882,030	B2	4/2005	Siniaguine	2010/0059869	A1	3/2010	Kaskoun et al.	
6,924,551	B2	8/2005	Rumer et al.	2010/0237386	A1	9/2010	Lin et al.	
6,962,867	B2	11/2005	Jackson et al.	2011/0095435	A1	4/2011	Volant et al.	
6,962,872	B2	11/2005	Chudzik et al.	2011/0108948	A1 *	5/2011	Kim et al. ....	257/532
7,030,481	B2	4/2006	Chudzik et al.	2011/0241185	A1	10/2011	Koester et al.	
7,049,170	B2	5/2006	Savastiouk et al.	2012/0061795	A1	3/2012	Yen et al.	
				2012/0261826	A1	10/2012	Kuo et al.	
				2012/0326319	A1	12/2012	Yu	

\* cited by examiner






FIG. 2A




FIG. 2B




FIG. 2C




FIG. 2D




FIG. 2E




FIG. 2F




FIG. 3A





FIG. 3B



ACTIVE DEVICE  
202

FIG. 4




FIG. 5

1

# THROUGH SILICON VIA (TSV) ISOLATION STRUCTURES FOR NOISE REDUCTION IN 3D INTEGRATED CIRCUIT

## RELATED APPLICATION

This application is a continuation of U.S. patent application Ser. No. 13/324,405, filed on Dec. 13, 2011, the contents of which are incorporated by reference as if set forth in their entirety.

## TECHNICAL FIELD

The disclosure relates, most generally, to semiconductor devices and methods for manufacturing the same and the disclosure is more particularly directed to 3D integrated circuits, and structures and methods for noise isolation for through silicon vias.

## BACKGROUND

3D (three dimensional) integrated circuits have become very popular in recent years due to the increased levels of integration they provide. 3D integrated circuits utilize through silicon via (TSV) structures which are via openings that extend completely through a semiconductor substrate and enable devices above and below the substrate to be coupled to one another and to devices internal to the substrate and provide the interconnects compatible with 3D wafer level packaging. When filled, the TSV structures may serve as signal lines or other purposes. Signal lines can carry and create significant amounts of electrical noise that adversely affects semiconductor devices such as active transistors, in their vicinity.

It would therefore be desirable to take advantage of the advanced integration levels afforded by 3D integrated circuits using TSV structures while avoiding problems associated with electrical noise created by such TSV structures.

## BRIEF DESCRIPTION OF THE DRAWING

The present disclosure is best understood from the following detailed description when read in conjunction with the accompanying drawing. It is emphasized that, according to common practice, the various features of the drawing are not necessarily to scale. On the contrary, the dimensions of the various features may be arbitrarily expanded or reduced for clarity. Like numerals denote like features throughout the specification and drawing.

FIG. 1 is a cross-sectional view showing an exemplary embodiment of a TSV isolation structure according to the disclosure;

FIGS. 2A-2F are cross-sectional views showing a sequence of processing operations for forming exemplary TSV isolation structures according to the disclosure;

FIGS. 3A and 3B are cross-sectional views illustrating features of another exemplary TSV isolation structure according to the disclosure;

FIG. 4 is a plan view showing a layout pattern of an array of TSV isolation structures providing isolation to an active, signal carrying TSV; and

FIG. 5 is another plan view showing a layout pattern of an array of TSV isolation structures providing isolation to an active, signal carrying TSV.

## DETAILED DESCRIPTION

FIG. 1 is a cross-sectional view showing one exemplary aspect of the disclosure. FIG. 1 shows semiconductor sub-

2

strate 2 which may be a P-type semiconductor substrate according to one exemplary embodiment and may be an N-type semiconductor substrate according to another exemplary embodiment. Semiconductor substrate 2 includes opposed surfaces including top surface 4 and opposed bottom surface 6. Semiconductor substrate 2 with bottom surface 6 is shown after a backgrinding or lapping process has been used to diminish the original thickness of semiconductor substrate 2 as will be shown in subsequent figures, for example in FIGS. 2A-2F. Still referring to FIG. 1, active through silicon via (TSV) 8 includes TSV opening 12 filled with conductive material 10 and carrying signal 14. Conductive material 10 may be copper, aluminum or other suitable materials and active TSV 8 enables wafer-to-wafer interconnect compatible with 3D wafer level packaging. Signal 14 may be a noisy signal. Noise is represented as electrical noise 16 which propagates through semiconductor substrate 2 and would adversely affect the performance of active semiconductor device 22 if not for the presence of isolation structure 20.

Active semiconductor device 22 includes transistor 24 in the illustrated embodiment but active semiconductor device 22 may be other active semiconductor devices in other exemplary embodiments. In exemplary embodiments in which active semiconductor device 22 is a transistor, it may be various different types of transistors such as a MOSFET (Metal Oxide Semiconductor Field Effect Transistor), a FinFET, or various other P-type or N-type transistors or other active semiconductor devices. The illustrated doping types and electrical connections of FIG. 1 are intended to be exemplary only.

Isolation structure 20 includes TSV isolation structure 23 which is formed of TSV opening 26 surrounded by surrounding dopant impurity region 28B and filled with conductive material 10. TSV openings 26 and 12 are formed simultaneously and may advantageously be filled with conductive material 10 simultaneously. The sidewalls of TSV openings 12 and 26 include oxide liner 30. Surrounding dopant impurity regions 28A and 28B surround TSV openings 12 and 26, respectively. The dopant impurity regions 28A, 28B may be P-type dopant impurity regions or N-type dopant impurity regions. In one embodiment, both dopant impurity regions 28A and 28B are P-type dopant impurity regions. In another embodiment, both dopant impurity regions 28A and 28B are N-type dopant impurity regions. In another embodiment, dopant impurity regions 28A and 28B are of different dopant impurity types. Surface dopant impurity region 32 may be an N-type dopant impurity region or a P-type dopant impurity region and will be the same dopant impurity type as surrounding dopant impurity region 28B according to various exemplary embodiments. In the illustrated embodiment, surface dopant impurity region 32 is advantageously a P+ dopant impurity region coupled to ground 34. According to the exemplary embodiment in which surface dopant impurity region 32 and surrounding dopant impurity region 28B are N-type dopant impurity regions, surface dopant impurity region 32 will be advantageously coupled to  $V_{DD}$ .

Still referring to FIG. 1, TSV isolation structure 23 is electrically coupled to surface dopant impurity region 32 and therefore also to ground 34 by conductive surface lead 38 because surrounding dopant impurity region 28B and surface dopant impurity region 32 are spaced apart, but it will be seen in other exemplary embodiments that surrounding dopant impurity region 28B may overlap surface dopant impurity region 32 and obviate the need for surface conductive lead 38.

Now turning to FIGS. 2A-2F, FIG. 2A shows semiconductor substrate 100 having top surface 102 and bottom surface 104. Semiconductor substrate 100 may be formed of silicon

or other suitable materials and it may be a P-type or N-type material. Active semiconductor device **108** is formed in and on top surface **102** and includes well region **110**, source/drain regions **112**, and gate **114** and active semiconductor device **108** is a transistor in the illustrated exemplary embodiment. Active semiconductor device **122** includes gate **124** and source/drain regions **126**. Active semiconductor devices **108**, **122** are intended to be exemplary only. Also formed extending downwardly from top surface **102** is surface dopant impurity region **118** which will be coupled to electrical coupling **120**, the dashed line indicating that the coupling has not yet been made. Surface dopant impurity region **118** may be an N-type dopant impurity region or it may be a P-type dopant impurity region. According to the embodiment in which surface dopant impurity region **118** is an N-type dopant impurity region, electrical coupling **120** will be to  $V_{DD}$  and according to the exemplary embodiment in which surface dopant impurity region **118** is a P-type dopant impurity region, electrical coupling **120** will be to ground.

FIG. 2B shows the structure of FIG. 2A after dielectric layer **130** has been formed over top surface **102**. Various suitable materials such as used as interlevel dielectric layers may be used as dielectric layer **130**. A photoresist layer may be formed over dielectric layer **130** and patterned and a subsequent etching process may be carried out to form the structure shown in FIG. 2C.

FIG. 2C shows the structure of FIG. 2B after via opening **134** has been formed extending downwardly from top surface **102**. Various etching processes may be used. Via opening **134** includes bottom **136** that does not reach bottom surface **104** at this stage of processing and also extends through dielectric layer **130**. Via opening **134** may include a width of about 4-10 microns and the width may be about 6 microns in one exemplary embodiment. Depth **140** may take on various values and may range from about 50-80 microns, preferably 60 microns, in one exemplary embodiment. It should be noted that the expressed values for the width and for depth **140**, are exemplary only. Via opening **134** is spaced from surface dopant impurity region **118** by spacing **142** which may be various distances in various exemplary embodiments. Spacing **142** will determine whether the surrounding dopant impurity region to be formed as shown in FIG. 2D, will overlap with surface dopant impurity region **118**. A further via opening (not shown) is advantageously formed to the left of via opening **134** in the illustration of FIG. 2C, the further via opening to serve as an active, signal carrying TSV (such as TSV opening **12** shown in FIG. 1) that will be isolated from active semiconductor devices **108**, **122** by the TSV isolation structure to be formed using via opening **134**.

FIG. 2D shows surrounding dopant impurity region **146** surrounding via opening **134** and extending downwardly to bottom **136**. Various methods may be used to form surrounding dopant impurity region **146** which may be an N-type or P-type region. In the exemplary embodiment, surrounding dopant impurity region **146** overlaps surface dopant impurity region **118** at overlap region **152**. Surrounding dopant impurity region **146** and surface dopant impurity region **118** will advantageously be of the same dopant type. In one exemplary embodiment, an angled ion implantation process may be used to introduce dopant impurities into substrate **100** around via opening **134** to form surrounding dopant impurity region **146**. This is illustrated by arrows **150** illustrative of an angled ion implantation process. Angled ion implantation processes are known in the art. According to another exemplary embodiment, a plasma doping operation may be used to form surrounding dopant impurity regions **146** and the plasma doping process may be carried out in-situ with the etching operation

used to form via opening **134**, or separately. According to either the angled ion implantation doping embodiment or the plasma doping embodiment, the doping operation may be carried out with patterned dielectric layer **130** still in place and also with a photoresist layer used to pattern dielectric layer **130**, still in place. Various other methods for introducing dopant impurities into sidewalls **138** of via opening **134** may be used. Surrounding dopant impurity region **146** may include various depths and in one exemplary embodiment, thickness **154** may range from about 10 to about 30 microns.

According to the embodiment in which a further via opening is advantageously formed to the left of via opening **134**, the doping operation simultaneously forms surrounding dopant impurity regions of the same impurity type around the further via opening, in one embodiment. The further via opening may be an active, signal carrying TSV such as TSV opening **12** shown in FIG. 1, in one embodiment. In another embodiment in which a further via opening (not shown) is advantageously formed to the left of via opening **134**, two separate doping operations may be used. In particular, two different doping operations may be used in conjunction with an interceding patterning operation, to separately form one of the surrounding dopant impurity regions to include a first impurity type and the other of the surrounding dopant impurity regions to include a second impurity type which may be the opposite impurity type.

The structure in FIG. 2E shows the structure of FIG. 2D after a thermal oxidation process has been carried out to form oxide liner **158** and after a backgrinding or backlapping operation has been carried out to upwardly recede the bottom surface of semiconductor substrate **100**. The thickness of semiconductor substrate **100** is diminished by the backgrinding or backlapping operation and backgrinded surface **160** results. The via opening (**134**) that had extended into semiconductor substrate **100** now extends completely through semiconductor substrate **100** forming TSV opening **164**.

TSV opening **164** will be substantially filled with a conductive material such as conductive material **168** such as shown in FIG. 2F. TSV isolation structure **170** includes oxide liner **158**, surrounding dopant impurity region **146** and TSV opening **164** filled with conductive material **168** and will serve as a TSV isolation structure **170** as it is coupled to electrical coupling **120** through substrate dopant impurity region **118**. In other exemplary embodiments, surrounding dopant impurity region **146** does not overlap with surface dopant impurity region **118**. When surface dopant impurity region **118** is an N-type dopant impurity region, electrical coupling **120** is to  $V_{DD}$  and when surface dopant impurity region **118** is a P-type dopant material, electrical coupling **120** will be ground. As discussed supra, TSV isolation structure **170** isolates active semiconductor devices **108**, **122** from electrical noise such as may be generated by a signal carrying active TSV disposed to the left of TSV isolation structure **170**.

According to the embodiment in which a further via opening (not shown in FIG. 2E) is formed to the left of via opening **134**, the thermal oxidation process and backgrinding or backlapping operations that are performed as described above, will also produce an oxide liner around the further via opening such as oxide liner **30** surrounding TSV opening **12** as in FIG. 1.

FIGS. 3A and 3B are cross-sectional views showing another exemplary embodiment, FIG. 3A representing the same step such as the processing step illustrated in FIG. 2D and FIG. 3B illustrating the same process step such as the process step illustrated in FIG. 2F. In FIG. 3A, depth **174** of surrounding dopant impurity region **146** is less than depth **140** of via opening **134**. FIG. 3A also shows the electrical con-

5

nection as ground connection **120A** such as used according to the exemplary embodiment in which surface dopant impurity region **118** is a P-type dopant impurity. The structure illustrated in FIG. **3B** is then produced after at least an oxidation process, a backgrinding process and a conductive material formation process are carried out upon the structure shown in FIG. **3A**. The exemplary structure shown in FIG. **3B** differs from the exemplary embodiment shown in FIG. **2F** because TSV isolation structure **170** including oxide liner **158** extends through semiconductor substrate **100** and reaches backgrinded surface **160**, however surrounding dopant impurity region **146** does not extend to backgrinded surface **160**. Depth **174** of surrounding dopant impurity region **146** is less than thickness **178** of the backgrinded semiconductor substrate **100**.

FIGS. **4** and **5** are top views illustrating two exemplary embodiments of arrays of TSV isolation structures used to isolate active TSV structures from active semiconductor devices. FIG. **4** shows array configuration **200** and FIG. **5** shows array configuration **220**. In each array, active TSVs **204** are separated from active semiconductor devices **202** by one or more TSV isolation structures arranged in an array. Active TSVs **204** are TSVs that carry signals or perform other active electrical functions and may include surrounding dopant impurity regions **210**, although surrounding dopant impurity regions **210** may not be present in some embodiments. In FIG. **4**, array configuration **200** includes a row of TSV isolation structures **206** including surrounding dopant impurity regions **216** and a row of TSV isolation structures **208** with surrounding dopant impurity regions **218**. FIG. **5** shows an inner ring of TSV isolation structures **206** with surrounding dopant impurity regions **216** and an outer ring of TSV isolation structures **208** with corresponding surrounding dopant impurity regions **218**.

Referring to FIGS. **4** and **5**, according to a first embodiment, TSV isolation structures **206** may be N-type TSV isolation structures with corresponding surrounding dopant impurity regions **216** being N-type dopant impurity regions coupled to  $V_{DD}$  with TSV isolation structures **208** being P-type TSV isolation structures with corresponding surrounding dopant impurity regions **218** being P-type dopant impurity regions coupled to ground. According to this first embodiment, surrounding dopant impurity region **210** may be either P-type or N-type dopant impurity regions. According to another exemplary embodiment, surrounding dopant impurity region **210**, and each of TSV isolation structures **206** and **208** and corresponding surrounding dopant impurity regions **216** and **218** are P-type dopant impurity regions coupled to ground. According to yet another exemplary embodiment, surrounding dopant impurity region **210**, and each of TSV isolation structures **206** and **208** and corresponding surrounding dopant impurity regions **216** and **218** are N-type dopant impurity regions coupled to  $V_{DD}$ . According to yet another exemplary embodiment, TSV isolation structures **206** may be P-type TSV isolation structures with corresponding surrounding dopant impurity regions **216** being P-type dopant impurity regions coupled to ground with TSV isolation structures **208** being N-type TSV isolation structures with corresponding surrounding dopant impurity regions **218** being N-type dopant impurity regions coupled to  $V_{DD}$ . According to this embodiment, surrounding dopant impurity regions **210** may be either P-type or N-type dopant impurity regions.

Active semiconductor device **202** may represent one or a plurality of any of various active semiconductor devices that may be formed within an integrated circuit and it should be understood that the configurations of the arrays shown in

6

FIGS. **4** and **5** are intended to be exemplary only and may take other shapes in other exemplary embodiments.

According to one aspect, a semiconductor device is provided. The semiconductor device comprises an active semiconductor device formed on a surface of a semiconductor substrate and an isolation through silicon via (TSV) extending through the semiconductor substrate and laterally spaced from the active semiconductor device and next to a surface dopant impurity region of a first dopant impurity type formed in the surface between the isolation TSV and the active semiconductor device. The semiconductor device further comprises an isolation TSV surrounded laterally by a surrounding dopant impurity region, the surrounding dopant impurity region being one of a P-type dopant impurity region coupled to ground and an N-type dopant impurity region coupled to  $V_{DD}$ .

According to another aspect, provided is a method for forming a semiconductor device. The method comprises: providing a semiconductor substrate with a surface having an active semiconductor device disposed thereon and a surface dopant impurity region of a first dopant impurity type disposed therein; forming a through silicon via (TSV) opening next to the surface dopant impurity region and extending downwardly from the surface and into the semiconductor substrate, the surface dopant impurity region disposed between the TSV opening and the active semiconductor device; forming a surrounding dopant impurity region surrounding the TSV opening, the surrounding dopant impurity region being one of a P-type dopant impurity region and an N-type dopant impurity region; and electrically coupling the surrounding dopant impurity region by one of coupling the P-type dopant impurity region to ground when the surrounding dopant impurity comprises a P-type dopant impurity region, and coupling the N-type dopant impurity region to  $V_{DD}$  when the surrounding dopant impurity comprises an N-type dopant impurity region.

According to another aspect, a method for forming a semiconductor device is provided. The method comprises providing a semiconductor substrate with a surface having an active semiconductor device disposed thereon; forming a plurality of through silicon vias (TSV) extending through the semiconductor substrate, the plurality of TSVs including an active TSV including a conductive structure carrying an electrical signal therein, an array of N-type TSV isolation structures surrounded by corresponding N-type surrounding dopant impurity regions and an array of P-type TSV isolation structures surrounded by corresponding P-type surrounding dopant impurity regions; and coupling the N-type TSV isolation structures to  $V_{DD}$  and coupling the P-type TSV isolation structures to ground, wherein the active TSV is separated from the active semiconductor device by at least some of the N-type TSV isolation structures and the P-type TSV isolation structures.

The preceding merely illustrates the principles of the disclosure. It will thus be appreciated that those skilled in the art will be able to devise various arrangements which, although not explicitly described or shown herein, embody the principles of the disclosure and are included within its spirit and scope. Furthermore, all examples and conditional language recited herein are principally intended expressly to be only for pedagogical purposes and to aid the reader in understanding the principles of the disclosure and the concepts contributed by the inventors to furthering the art, and are to be construed as being without limitation to such specifically recited examples and conditions. Moreover, all statements herein reciting principles, aspects, and embodiments of the disclosure, as well as specific examples thereof, are intended to

7

encompass both structural and functional equivalents thereof. Additionally, it is intended that such equivalents include both currently known equivalents and equivalents developed in the future, i.e., any elements developed that perform the same function, regardless of structure.

This description of the exemplary embodiments is intended to be read in connection with the figures of the accompanying drawing, which are to be considered part of the entire written description. In the description, relative terms such as “lower,” “upper,” “horizontal,” “vertical,” “above,” “below,” “up,” “down,” “top” and “bottom” as well as derivatives thereof (e.g., “horizontally,” “downwardly,” “upwardly,” etc.) should be construed to refer to the orientation as then described or as shown in the drawing under discussion. These relative terms are for convenience of description and do not require that the apparatus be constructed or operated in a particular orientation. Terms concerning attachments, coupling and the like, such as “connected” and “interconnected,” refer to a relationship wherein structures are secured or attached to one another either directly or indirectly through intervening structures, as well as both movable or rigid attachments or relationships, unless expressly described otherwise.

Although the disclosure has been described in terms of exemplary embodiments, it is not limited thereto. Rather, the appended claims should be construed broadly, to include other variants and embodiments of the disclosure, which may be made by those skilled in the art without departing from the scope and range of equivalents of the disclosure.

What is claimed is:

1. A semiconductor device comprising:
  - an active semiconductor device formed on a surface of a semiconductor substrate;
  - an isolation through silicon via (TSV) extending through said semiconductor substrate and laterally spaced from said active semiconductor device and next to a surface dopant impurity region of a first dopant impurity type disposed in said surface between said isolation TSV and said active semiconductor device, said surface dopant impurity region having a dopant concentration different from said substrate; and
  - said isolation TSV surrounded laterally by a surrounding dopant impurity region along part of a length of said isolation TSV, wherein said surrounding dopant impurity region extends from said surface to a termination location above a bottom surface of said semiconductor substrate.
2. The semiconductor device as in claim 1, wherein said surrounding dopant impurity region is one of a P-type dopant impurity region and an N-type dopant impurity region.
3. The semiconductor device as in claim 1, further including an oxide liner laterally surrounding said isolation TSV, wherein said surrounding dopant impurity region surrounds said oxide liner along a part of a length of said oxide liner.
4. The semiconductor device as in claim 1, further comprising an active TSV containing a conductive line carrying a signal and extending through said semiconductor substrate, said isolation TSV interposed between said active TSV and said active semiconductor device and wherein said active semiconductor device comprises a transistor.
5. The semiconductor device as in claim 4, further comprising a plurality of further isolation TSVs forming an array, said active TSV surrounded by said array and isolated from said transistor by said array.

8

6. The semiconductor device as in claim 4, wherein said active TSV includes an oxide liner formed on sidewalls thereof and a surrounding dopant impurity region that laterally surrounds said oxide liner.

7. The semiconductor device as in claim 1, wherein said first dopant impurity type comprises P-type, said surrounding dopant impurity region comprises said P-type dopant impurity region coupled to ground and overlaps with said surface dopant impurity region of said first dopant impurity type, and said isolation TSV contains a copper lead therein.

8. The semiconductor device as in claim 1, wherein said first dopant impurity type comprises N-type and said surrounding dopant impurity region comprises said N-type dopant impurity region coupled to  $V_{DD}$ .

9. The semiconductor device as in claim 8, wherein said surrounding dopant impurity region overlaps with said surface dopant impurity region of said first dopant impurity type, said semiconductor substrate comprises a P-type material, said isolation TSV is coupled to  $V_{DD}$  through said surface dopant impurity which is coupled to  $V_{DD}$ , and said isolation TSV contains a copper lead therein.

10. The semiconductor device as in claim 1, wherein said isolation TSV is a P-type isolation TSV with said surrounding dopant impurity region comprising said P-type dopant impurity region coupled to ground and said first dopant impurity type comprising P-type and further comprising:

a plurality of further of said P-type isolation TSVs and a plurality of N-type isolation TSVs, each said N-type isolation TSV having said surrounding dopant impurity region being an N-type dopant impurity region disposed next to a further N-type dopant impurity region and coupled to  $V_{DD}$ ;

an active TSV structure containing a conductive lead, carrying a signal and extending through said substrate, and wherein said active TSV structure is surrounded by an array of said N-type isolation TSVs and said array of N-type isolation TSVs is surrounded by an array of said P-type isolation TSVs.

11. A semiconductor device comprising:

an active semiconductor device formed on a surface of a semiconductor substrate;

an isolation through silicon via (TSV) extending through said semiconductor substrate, said isolation TSV laterally spaced from said active semiconductor device;

a surface dopant impurity region of a first dopant impurity type disposed in said surface between said isolation TSV and said active semiconductor device, said surface dopant impurity region having a dopant concentration different from said substrate;

an oxide liner laterally surrounding said isolation TSV; and

a surrounding dopant impurity region laterally surrounding the oxide liner along a part of a length of the oxide liner, wherein said surrounding dopant impurity region extends from said surface to a termination location above a bottom surface of said semiconductor substrate.

12. The semiconductor device of claim 11, further comprising an active TSV containing a conductive line carrying a signal and extending through said semiconductor substrate, said isolation TSV interposed between said active TSV and said active semiconductor device and wherein said active semiconductor device comprises a transistor.

13. The semiconductor device as in claim 12, further comprising a plurality of further isolation TSVs forming an array, said active TSV surrounded by said array and isolated from said transistor by said array.

14. The semiconductor device as in claim 12, wherein said active TSV includes an oxide liner formed on sidewalls thereof and a surrounding dopant impurity region that laterally surrounds said oxide liner.

15. The semiconductor device as in claim 11, wherein said first dopant impurity type comprises P-type, said surrounding dopant impurity region comprises said P-type dopant impurity region coupled to ground and overlaps with said surface dopant impurity region of said first dopant impurity type, and said isolation TSV contains a copper lead therein.

16. The semiconductor device as in claim 11, wherein: said first dopant impurity type comprises N-type and said surrounding dopant impurity region comprises said N-type dopant impurity region coupled to VDD, and said surrounding dopant impurity region overlaps with said surface dopant impurity region of said first dopant impurity type, said semiconductor substrate comprises a P-type material, said isolation TSV is coupled to VDD through said surface dopant impurity which is coupled to VDD, and said isolation TSV contains a copper lead therein.

17. The semiconductor device as in claim 11, wherein said isolation TSV is a P-type isolation TSV with said surrounding dopant impurity region comprising said P-type dopant impurity region coupled to ground and said first dopant impurity type comprising P-type and further comprising:

a plurality of further of said P-type isolation TSVs and a plurality of N-type isolation TSVs, each said N-type isolation TSV having said surrounding dopant impurity region being an N-type dopant impurity region disposed next to a further N-type dopant impurity region and coupled to  $V_{DD}$ ;

an active TSV structure containing a conductive lead, carrying a signal and extending through said substrate, and wherein said active TSV structure is surrounded by an array of said N-type isolation TSVs and said array of N-type isolation TSVs is surrounded by an array of said P-type isolation TSVs.

18. A semiconductor device comprising: an active semiconductor device formed on a surface of a semiconductor substrate;

an isolation through silicon via (TSV) extending through said semiconductor substrate, said isolation TSV laterally spaced from said active semiconductor device;

a surface dopant impurity region of a first dopant impurity type disposed in said surface between said isolation TSV and said active semiconductor device, said surface dopant impurity region having a dopant concentration different from said substrate;

an oxide liner laterally surrounding said isolation TSV, and extending from the surface to a bottom surface of the semiconductor substrate; and

a surrounding dopant impurity region laterally surrounding the oxide liner along a part of a length of the oxide liner, wherein said surrounding dopant impurity region extends from said surface to a termination location above the bottom surface of said semiconductor substrate.

19. The semiconductor device of claim 18, wherein the surface dopant impurity region extends from said surface to a termination location above the termination location of the surrounding dopant impurity region.

20. The semiconductor device of claim 19, wherein said surrounding dopant impurity region comprises a P-type dopant impurity region coupled to ground and said first dopant impurity type comprises P-type, the device further comprising:

a plurality of additional ones of said isolation TSVs; an active TSV structure containing a conductive lead, carrying a signal and extending through said substrate, wherein said isolation TSV and said plurality of additional isolation TSVs are located between the active semiconductor device and the active TSV structure.

\* \* \* \* \*